



State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
<i>UPLAND</i>								
AL	28	62.7	52.4	63,144	28	69.9	58.1	288,413
AR	29	95.4	88.3	140,870	29	96.1	88.8	744,427
AZ	10	72.8	51.1	25,535	10	80.4	49.9	102,094
CA	10	92.2	78.5	15,759	10	93.1	80.1	54,933
FL	4	48.4	45.4	10,620	4	52.5	49.6	26,560
GA	55	55.7	47.5	173,759	56	62.1	53.3	616,521
KS	3	36.5	24.7	9,938	3	37.8	23.4	19,938
LA	16	86.2	69.3	36,250	18	87.7	70.9	272,921
MO	19	96.1	85.5	68,486	19	94.0	83.1	278,769
MS	37	83.6	58.7	127,566	37	86.6	63.3	725,205
NC	32	94.5	85.9	60,830	32	94.2	83.7	148,369
NM	2	92.9	76.8	2,581	2	93.8	75.0	6,071
OK	11	82.8	70.5	33,480	11	85.9	73.9	130,761
SC	15	93.3	87.2	21,869	15	93.1	85.3	67,958
TN	21	93.1	79.3	79,276	21	89.2	69.5	342,819
TX	149	70.9	55.6	431,485	171	80.9	66.7	2,888,632
VA	4	92.0	82.3	13,333	4	92.1	82.6	20,013
<b>United States</b>	<b>445</b>	<b>77.3</b>	<b>64.0</b>	<b>1,314,781</b>	<b>470</b>	<b>82.6</b>	<b>68.6</b>	<b>6,734,404</b>
<i>AMERICAN PIMA</i>								
AZ*	-			-	-			-
CA	11			42,447	12			120,913
NM*	-			-	-			-
TX	2			3,856	2			8,889
United States	15			48,890	16			133,812
<b>United States all cotton</b>	<b>456</b>			<b>1,363,671</b>	<b>481</b>			<b>6,868,216</b>

\* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE  
For The Week Ending Nov 19, 2020**

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 11 & 21	1-2	Pct. *	Pct. 0.2	Pct. 0.3	Pct. 0.3	Pct. 80.8	Pct. 79.5	Pct. 44.8	Pct. 56.1	Pct. -	Pct. *	Pct. 0.3	Pct. 0.2
	3	0.2	0.3	0.1	0.3	6.3	4.2	9.2	8.6	*	*	0.7	0.3
	4	0.1	*	*	*	0.2	0.1	0.2	0.7	-	-	*	*
	5	*	*	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>0.3</b>	<b>0.6</b>	<b>0.4</b>	<b>0.6</b>	<b>87.3</b>	<b>83.8</b>	<b>54.2</b>	<b>65.5</b>	<b>*</b>	<b>*</b>	<b>1.0</b>
31	1-2	1.7	1.9	0.8	2.1	5.5	2.9	23.3	19.5	1.0	1.0	1.6	1.7
	3	14.4	17.3	6.9	17.2	4.7	2.8	16.4	10.6	8.6	10.1	17.4	15.0
	4	8.7	11.0	3.1	8.5	1.2	0.7	1.6	1.8	6.1	5.0	9.0	7.1
	5	1.0	1.0	0.1	0.4	0.1	*	*	0.1	0.4	0.3	0.6	0.4
	6	*	*	-	*	-	-	-	-	-	-	*	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>25.8</b>	<b>31.1</b>	<b>11.0</b>	<b>28.3</b>	<b>11.5</b>	<b>6.5</b>	<b>41.2</b>	<b>32.1</b>	<b>16.1</b>	<b>16.5</b>	<b>28.7</b>
41	1-2	1.0	0.6	0.7	0.5	*	*	0.2	0.2	0.3	0.3	0.5	0.5
	3	22.0	16.0	24.5	18.1	*	0.2	1.6	0.7	13.0	14.0	18.3	17.3
	4	29.3	26.4	44.3	37.7	0.1	0.1	0.5	0.2	40.0	34.1	28.3	27.9
	5	6.9	7.3	11.0	10.8	0.2	0.1	*	*	10.5	10.2	6.2	6.5
	6	0.4	0.5	0.5	0.6	*	*	-	-	0.7	0.8	0.3	0.4
	7	*	*	*	*	*	*	-	-	*	*	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	*
	<b>Total</b>	----	<b>59.6</b>	<b>50.9</b>	<b>80.9</b>	<b>67.7</b>	<b>0.4</b>	<b>0.4</b>	<b>2.3</b>	<b>1.2</b>	<b>64.5</b>	<b>59.5</b>	<b>53.7</b>
51	1-2	*	*	*	*	-	-	-	-	*	*	*	*
	3	0.5	0.4	0.7	0.2	-	-	-	-	1.2	0.9	0.5	0.4
	4	2.2	1.6	3.4	1.3	-	-	-	-	5.6	4.2	2.4	1.8
	5	1.1	1.2	1.8	0.8	-	-	-	-	2.8	2.2	1.6	1.4
	6	0.2	0.2	0.2	0.1	-	-	-	-	0.3	0.3	0.3	0.3
	7	*	*	*	*	-	-	-	-	*	*	*	*
	8	-	-	-	-	*	*	-	-	-	-	-	-
	<b>Total</b>	----	<b>4.0</b>	<b>3.4</b>	<b>6.1</b>	<b>2.5</b>	<b>*</b>	<b>*</b>	<b>-</b>	<b>-</b>	<b>9.9</b>	<b>7.7</b>	<b>4.9</b>
61	1-2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	*	-	-	-	-	-	-	*	*
	4	*	*	-	-	-	-	-	-	-	-	*	*
	5	*	*	-	-	-	-	-	-	-	-	*	*
	6	-	-	-	-	-	-	-	-	-	-	*	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>*</b>	<b>*</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>*</b>
71	1-2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	*	*	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>-</b>	<b>-</b>	<b>*</b>	<b>*</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>
12 & 22	1-2	-	*	-	*	0.1	7.2	*	0.2	-	-	-	*
	3	*	*	-	*	0.2	1.5	0.1	0.1	-	-	*	*
	4	-	*	-	-	0.1	0.1	0.1	*	-	-	-	*
	5	-	-	-	-	*	*	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>*</b>	<b>*</b>	<b>-</b>	<b>*</b>	<b>0.4</b>	<b>8.8</b>	<b>0.2</b>	<b>0.3</b>	<b>-</b>	<b>-</b>	<b>*</b>
32	1-2	*	0.1	*	*	*	0.1	1.1	0.5	-	*	*	0.1
	3	0.3	1.0	0.1	0.1	0.1	0.1	0.7	0.3	0.1	0.2	0.2	0.7
	4	0.5	0.8	0.1	0.1	0.2	0.1	0.1	*	0.2	0.1	0.1	0.3
	5	0.1	0.1	*	*	*	*	-	-	*	*	*	*
	6	-	*	-	-	*	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>0.9</b>	<b>2.0</b>	<b>0.2</b>	<b>0.2</b>	<b>0.3</b>	<b>0.3</b>	<b>1.8</b>	<b>0.8</b>	<b>0.4</b>	<b>0.4</b>	<b>0.4</b>
42	1-2	0.1	0.1	-	*	-	*	*	*	-	0.1	0.1	0.1
	3	1.7	2.2	0.1	0.1	*	*	0.1	0.1	0.6	1.8	1.7	3.7
	4	3.3	4.1	0.7	0.4	-	-	0.1	*	2.7	3.5	3.1	5.7
	5	1.0	1.4	0.3	0.2	*	*	-	-	0.5	0.9	0.8	1.3
	6	0.1	0.1	*	*	-	-	-	-	*	0.1	0.1	0.1
	7	-	*	-	-	-	-	-	-	-	-	*	*
	8	-	-	-	-	*	*	-	-	-	-	-	-
	<b>Total</b>	----	<b>6.2</b>	<b>7.9</b>	<b>1.1</b>	<b>0.7</b>	<b>*</b>	<b>*</b>	<b>0.2</b>	<b>0.1</b>	<b>3.9</b>	<b>6.4</b>	<b>5.8</b>

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Nov 19, 2020**

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 52	1-2	*	*	-	*	-	-	-	-	*	*	*	*
	3	0.4	0.5	*	*	-	-	*	*	0.7	1.4	0.5	0.5
	4	1.1	1.2	*	*	-	-	-	-	2.1	4.0	1.9	1.9
	5	0.5	0.8	*	*	-	-	-	-	1.4	1.8	1.4	1.4
	6	0.2	0.2	*	*	-	-	-	-	0.2	0.2	0.4	0.3
	7	*	*	*	*	-	-	-	-	-	*	0.1	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>2.2</b>	<b>2.8</b>	<b>0.1</b>	<b>*</b>	-	-	<b>*</b>	<b>*</b>	<b>4.5</b>	<b>7.4</b>	<b>4.2</b>
62	1-2	-	-	-	-	-	-	-	-	-	-	-	-
	3	*	*	-	-	-	-	-	-	-	-	*	*
	4	0.1	0.1	-	*	-	-	-	-	-	*	*	*
	5	*	0.1	-	-	-	-	-	-	-	*	0.1	*
	6	*	*	-	-	-	-	-	-	-	-	0.1	*
	7	-	*	-	-	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	*
	<b>Total</b>	----	<b>0.1</b>	<b>0.2</b>	-	<b>*</b>	-	-	-	-	-	<b>*</b>	<b>0.2</b>
13 & 23	1-2	-	-	-	-	*	0.1	-	*	-	-	-	-
	3	-	*	-	-	*	*	-	-	-	-	*	*
	4	-	*	-	-	-	*	-	-	-	-	*	*
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	-	<b>*</b>	-	-	<b>*</b>	<b>0.1</b>	-	<b>*</b>	-	-	<b>*</b>
33	1-2	-	*	-	-	*	*	*	*	-	-	*	*
	3	*	*	*	*	-	*	-	*	-	*	*	*
	4	*	*	*	*	*	*	-	-	*	*	*	*
	5	*	*	-	*	*	*	-	-	*	*	*	*
	6	-	-	-	-	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>0.1</b>	<b>*</b>	<b>*</b>	<b>*</b>	<b>*</b>	<b>*</b>	<b>*</b>	<b>*</b>	<b>*</b>	<b>0.1</b>	<b>*</b>
43	1-2	*	*	-	-	-	-	-	-	-	0.1	*	*
	3	*	0.1	*	*	-	-	-	-	0.1	0.4	0.1	0.3
	4	0.2	0.2	0.1	*	-	*	*	*	0.4	0.3	0.2	0.4
	5	0.1	0.1	*	*	-	*	-	-	-	*	0.1	0.1
	6	*	*	*	*	-	-	-	-	-	-	*	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>0.3</b>	<b>0.3</b>	<b>0.1</b>	<b>*</b>	-	<b>*</b>	<b>*</b>	<b>*</b>	<b>0.5</b>	<b>0.7</b>	<b>0.4</b>
53	1-2	-	*	-	*	-	-	-	-	-	*	*	*
	3	*	0.1	*	*	-	-	-	-	*	0.5	0.1	0.1
	4	0.1	0.2	*	*	-	-	-	-	0.1	0.5	0.3	0.4
	5	0.1	0.1	*	*	-	-	-	-	*	0.1	0.2	0.3
	6	*	*	-	-	-	-	-	-	*	*	0.1	0.1
	7	*	*	-	-	-	-	-	-	-	-	*	*
	8	-	*	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>0.2</b>	<b>0.5</b>	<b>*</b>	<b>*</b>	-	-	-	-	<b>0.2</b>	<b>1.2</b>	<b>0.6</b>
63	1-2	*	*	-	-	-	-	-	-	-	-	-	-
	3	*	*	-	-	-	-	-	-	-	-	*	*
	4	0.1	0.1	-	-	-	-	-	-	-	*	*	*
	5	0.1	0.1	-	*	-	-	-	-	-	-	*	*
	6	*	*	-	-	-	-	-	-	-	-	*	*
	7	-	*	-	-	-	-	-	-	-	*	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	*
	<b>Total</b>	----	<b>0.2</b>	<b>0.2</b>	-	<b>*</b>	-	-	-	-	-	<b>*</b>	<b>0.1</b>
24 - 54	1-8	*	*	*	*	-	-	-	-	-	0.1	*	0.1
25 - 35	1-8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1-8	*	*	-	-	-	-	-	-	-	-	*	*
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	-
31		*	*	-	-	-	*	-	-	*	*	*	*
32		*	*	-	-	*	*	-	*	-	*	*	0.1
33		0.1	0.2	*	*	0.7	0.4	*	*	0.2	0.5	0.2	0.4
34		0.8	1.6	*	*	2.7	2.4	*	0.4	1.0	1.9	1.2	2.2
35		3.6	5.6	0.5	0.4	13.9	11.2	0.3	4.0	1.8	3.8	4.8	7.4
36		11.8	13.7	3.2	2.7	20.9	24.1	8.8	18.5	7.4	8.2	13.3	16.7
37		31.7	31.5	21.7	21.4	33.1	33.6	32.2	29.6	20.2	23.4	30.6	32.6
38		31.3	28.2	23.1	23.4	21.1	20.1	40.3	28.5	41.0	41.2	28.7	25.3
39		16.6	15.1	28.0	28.2	7.0	7.3	15.8	17.1	26.7	19.8	17.4	12.9
40 & Longer		4.0	4.0	23.5	24.0	0.5	0.8	2.5	1.8	1.8	1.2	3.9	2.5
<b>Average Staple</b>		<b>37.55</b>	<b>37.40</b>	<b>38.49</b>	<b>38.52</b>	<b>36.77</b>	<b>36.81</b>	<b>37.70</b>	<b>37.40</b>	<b>37.85</b>	<b>37.61</b>	<b>37.49</b>	<b>37.18</b>
<b>Average Length</b>		<b>1.17</b>	<b>1.17</b>	<b>1.20</b>	<b>1.20</b>	<b>1.15</b>	<b>1.15</b>	<b>1.18</b>	<b>1.17</b>	<b>1.18</b>	<b>1.18</b>	<b>1.17</b>	<b>1.16</b>

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE  
For The Week Ending Nov 19, 2020**

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1-2	41.0	34.1	0.6	1.9	0.1	1.2	0.4	0.9	0.2	0.2	95.4	91.7
	3	20.0	24.0	0.9	3.9	0.2	0.6	0.3	1.3	0.3	0.3	1.9	2.3
	4	2.4	3.3	*	0.2	*	*	*	0.1	*	*	-	-
	5	0.1	*	-	*	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	<b>63.5</b>	<b>61.5</b>	<b>1.5</b>	<b>6.1</b>	<b>0.3</b>	<b>1.8</b>	<b>0.7</b>	<b>2.2</b>	<b>0.5</b>	<b>0.5</b>	<b>97.4</b>	<b>93.9</b>
31	1-2	0.9	1.1	1.0	1.5	1.7	8.8	2.0	2.6	4.1	4.9	2.0	3.0
	3	11.3	11.8	14.3	18.6	8.6	22.2	10.6	19.7	24.7	26.2	0.6	0.6
	4	12.2	14.2	8.3	11.9	2.4	5.3	5.3	12.1	9.0	9.1	-	*
	5	2.6	2.8	0.5	0.6	0.1	0.3	0.4	1.0	0.3	0.5	-	-
	6	0.2	0.2	*	*	-	*	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	<b>27.2</b>	<b>30.1</b>	<b>24.1</b>	<b>32.5</b>	<b>12.9</b>	<b>36.5</b>	<b>18.4</b>	<b>35.4</b>	<b>38.2</b>	<b>40.7</b>	<b>2.6</b>	<b>3.6</b>
41	1-2	-	*	0.5	0.4	2.5	1.5	1.1	0.5	1.2	1.3	-	-
	3	0.1	0.1	20.3	15.0	34.4	23.9	22.2	14.1	28.3	27.1	-	-
	4	0.3	0.4	34.9	29.9	37.9	28.3	39.0	31.5	25.2	23.1	-	-
	5	0.3	0.7	8.2	6.6	4.9	4.6	11.1	10.5	3.0	3.3	*	*
	6	0.2	0.8	0.6	0.3	0.1	0.1	0.6	0.7	0.1	0.1	-	-
	7	0.1	0.5	*	*	-	-	*	*	-	-	-	-
	8	0.1	0.2	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	<b>1.0</b>	<b>2.6</b>	<b>64.6</b>	<b>52.1</b>	<b>79.8</b>	<b>58.4</b>	<b>74.0</b>	<b>57.2</b>	<b>57.9</b>	<b>54.9</b>	<b>*</b>	<b>*</b>
51	1-2	-	-	-	*	*	*	*	*	-	*	-	-
	3	-	-	0.2	0.2	0.9	0.3	0.2	0.1	*	*	-	-
	4	-	-	0.9	0.9	3.7	1.6	1.3	0.8	0.2	0.1	-	-
	5	-	-	0.3	0.3	2.0	0.8	1.1	0.8	*	*	-	-
	6	-	-	0.1	*	0.1	*	0.2	0.2	*	*	-	-
	7	*	*	*	*	*	*	*	*	-	-	-	-
	8	0.1	0.1	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	<b>0.2</b>	<b>0.1</b>	<b>1.5</b>	<b>1.4</b>	<b>6.7</b>	<b>2.8</b>	<b>2.8</b>	<b>1.9</b>	<b>0.2</b>	<b>0.2</b>	<b>-</b>	<b>-</b>
61	1-2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-	-	-
	4	-	-	-	*	-	-	-	*	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	<b>-</b>	<b>-</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>
71	1-2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>
12 & 22	1-2	0.2	0.1	-	*	-	-	-	*	*	*	-	1.5
	3	0.7	0.5	-	*	-	*	*	*	*	*	-	0.1
	4	0.3	0.2	-	*	*	*	*	*	-	*	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	<b>1.1</b>	<b>0.9</b>	<b>-</b>	<b>0.1</b>	<b>*</b>	<b>*</b>	<b>*</b>	<b>*</b>	<b>*</b>	<b>*</b>	<b>-</b>	<b>1.7</b>
32	1-2	*	*	*	0.1	*	*	*	*	*	0.1	-	*
	3	0.4	0.3	0.5	0.8	*	*	0.3	0.3	0.4	0.5	-	-
	4	1.5	1.0	0.4	0.6	*	*	0.2	0.3	0.2	0.3	*	*
	5	1.5	1.0	0.1	0.1	-	*	*	0.1	*	*	-	-
	6	0.5	0.3	*	*	-	-	-	*	*	*	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	<b>3.9</b>	<b>2.5</b>	<b>0.9</b>	<b>1.5</b>	<b>0.1</b>	<b>0.1</b>	<b>0.6</b>	<b>0.7</b>	<b>0.6</b>	<b>1.0</b>	<b>*</b>	<b>*</b>
42	1-2	-	-	*	*	*	*	0.1	*	*	0.1	-	-
	3	-	*	0.8	1.0	0.1	0.1	1.0	0.5	0.6	0.9	-	-
	4	*	*	3.0	3.1	0.1	0.2	1.3	1.1	1.1	1.1	-	-
	5	0.1	0.1	1.3	1.0	*	*	0.8	0.6	0.2	0.3	-	-
	6	0.1	0.1	0.2	0.1	*	*	0.1	0.1	*	*	-	-
	7	*	*	*	*	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	<b>0.2</b>	<b>0.2</b>	<b>5.4</b>	<b>5.3</b>	<b>0.2</b>	<b>0.3</b>	<b>3.2</b>	<b>2.3</b>	<b>2.0</b>	<b>2.4</b>	<b>-</b>	<b>-</b>

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Nov 19, 2020**

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 52	1 - 2	-	-	-	*	-	-	-	*	-	-	-	-
	3	-	-	0.3	0.1	*	*	*	*	*	*	-	-
	4	-	-	1.1	0.3	*	*	0.1	0.1	0.1	*	-	-
	5	-	-	0.2	0.1	*	*	0.1	0.1	*	*	-	-
	6	-	-	*	*	*	*	*	*	-	*	-	-
	7	-	-	*	*	*	*	-	*	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	-	*	<b>1.6</b>	<b>0.5</b>	<b>*</b>	<b>*</b>	<b>0.2</b>	<b>0.2</b>	<b>0.1</b>	<b>0.1</b>	-
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	-	-	*	-	-	-	-
	5	-	-	-	*	-	-	*	*	-	-	-	-
	6	-	-	-	*	-	-	*	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	-	-	-	*	-	-	<b>*</b>	<b>*</b>	-	-	-
13 & 23	1 - 2	-	-	-	-	-	-	-	-	-	*	-	0.2
	3	0.1	0.1	-	-	-	-	-	-	-	-	-	0.2
	4	*	*	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>0.1</b>	<b>0.1</b>	-	-	-	-	-	-	-	<b>*</b>	-
33	1 - 2	-	-	*	*	*	*	*	*	*	*	-	*
	3	0.1	0.1	-	*	-	*	*	*	0.1	*	-	0.3
	4	0.9	0.5	*	*	-	*	*	*	0.1	*	-	-
	5	0.6	0.4	-	*	-	*	-	*	*	*	-	-
	6	0.1	0.1	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>1.8</b>	<b>1.1</b>	<b>*</b>	<b>0.1</b>	<b>*</b>	<b>*</b>	<b>*</b>	<b>*</b>	<b>0.2</b>	<b>0.1</b>	-
43	1 - 2	*	*	-	*	*	*	*	*	*	*	-	-
	3	-	-	*	*	*	*	0.1	*	0.1	*	-	*
	4	*	*	0.2	0.2	*	*	*	*	0.2	0.1	-	*
	5	0.3	0.2	0.1	0.1	*	*	*	*	0.1	*	-	-
	6	0.2	0.1	*	*	-	-	-	*	*	*	-	-
	7	*	*	*	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>0.5</b>	<b>0.3</b>	<b>0.4</b>	<b>0.3</b>	<b>*</b>	<b>*</b>	<b>0.1</b>	<b>0.1</b>	<b>0.3</b>	<b>0.2</b>	-
53	1 - 2	-	-	-	-	-	-	-	*	-	-	-	-
	3	-	-	-	*	-	-	*	*	-	-	-	-
	4	-	-	*	*	*	*	*	*	*	*	-	-
	5	-	*	0.1	*	*	*	*	*	*	*	-	-
	6	-	*	*	*	-	-	*	*	*	*	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>*</b>	<b>0.1</b>	<b>0.1</b>	<b>*</b>	<b>*</b>	<b>*</b>	<b>*</b>	<b>*</b>	<b>*</b>	<b>*</b>	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	-	-	*	*	*	-	-
	5	-	-	-	-	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	-	-	-	-	-	-	-	<b>*</b>	<b>*</b>	<b>*</b>	-
24 - 54	1 - 8	0.5	0.5	*	*	-	-	*	*	*	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	
81 - 85	1 - 8	-	0.1	-	-	-	-	-	*	-	-	-	
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	-
31		0.2	0.1	-	-	-	-	-	-	-	-	-	-
32		0.3	0.6	-	-	-	-	*	*	*	*	-	-
33		5.6	3.3	-	*	*	*	*	*	*	*	-	*
34		22.5	18.5	0.1	0.2	*	*	0.3	0.2	0.2	0.2	0.1	0.1
35		33.0	40.3	1.2	0.9	*	0.1	2.2	1.5	2.6	2.1	8.7	10.0
36		29.1	28.1	3.1	3.1	1.3	1.5	6.0	5.4	11.1	9.7	21.9	29.1
37		6.6	7.6	15.4	15.9	27.9	24.2	21.4	18.2	36.8	35.9	29.8	28.8
38		2.5	1.5	25.9	26.1	29.1	27.3	21.4	24.8	22.6	24.1	15.4	14.9
39		-	*	30.6	32.0	26.9	28.7	28.2	30.8	18.3	19.6	18.2	13.6
40 & Longer		-	-	23.6	21.8	14.6	18.2	20.4	19.0	8.4	8.3	5.9	3.4
<b>Average Staple</b>		<b>35.14</b>	<b>35.21</b>	<b>38.58</b>	<b>38.54</b>	<b>38.27</b>	<b>38.40</b>	<b>38.29</b>	<b>38.37</b>	<b>37.68</b>	<b>37.74</b>	<b>37.30</b>	<b>37.03</b>
<b>Average Length</b>		<b>1.09</b>	<b>1.10</b>	<b>1.21</b>	<b>1.21</b>	<b>1.20</b>	<b>1.20</b>	<b>1.20</b>	<b>1.20</b>	<b>1.18</b>	<b>1.18</b>	<b>1.16</b>	<b>1.16</b>

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Nov 19, 2020**

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA		
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	
Color 11 & 21	1-2	53.1	69.1	0.5	0.5	0.3	4.4	62.1	39.8	0.1	*	
	3	11.1	7.2	0.9	0.7	0.2	1.3	13.6	12.0	0.2	0.2	
	4	0.2	0.1	*	*	*	*	1.5	1.0	*	*	
	5	-	-	-	-	-	-	0.1	*	-	-	
	6	-	-	-	*	-	-	-	*	-	-	
	7	-	-	-	-	-	-	-	-	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	<b>Total</b>	----	<b>64.4</b>	<b>76.5</b>	<b>1.5</b>	<b>1.2</b>	<b>0.5</b>	<b>5.7</b>	<b>77.3</b>	<b>52.8</b>	<b>0.3</b>	<b>0.2</b>
	31	1-2	7.6	6.4	1.7	2.3	12.5	18.1	1.5	3.2	0.9	2.1
3		17.3	9.4	25.9	23.1	30.2	39.7	4.6	14.2	7.4	8.2	
4		3.3	2.3	16.9	11.9	7.0	7.5	3.1	6.0	2.2	2.0	
5		0.3	0.2	1.5	0.8	0.2	0.2	0.9	0.7	*	0.2	
6		*	*	*	*	*	*	0.1	0.1	-	*	
7		-	-	-	-	-	-	*	*	-	-	
8		-	-	-	-	-	-	*	*	-	-	
<b>Total</b>		----	<b>28.6</b>	<b>18.4</b>	<b>46.0</b>	<b>38.2</b>	<b>49.9</b>	<b>65.5</b>	<b>10.2</b>	<b>24.1</b>	<b>10.5</b>	<b>12.5</b>
41		1-2	*	*	0.4	0.3	2.7	1.5	0.3	0.7	5.0	6.0
	3	0.1	0.1	11.3	14.8	24.4	13.3	1.7	4.7	49.4	48.8	
	4	0.6	0.3	26.9	32.0	19.0	10.3	1.0	3.7	27.5	24.7	
	5	0.5	0.3	10.4	9.3	2.4	1.3	0.4	0.8	2.1	1.7	
	6	0.3	0.1	0.6	0.5	0.1	*	0.3	0.2	*	*	
	7	*	*	-	-	-	-	0.2	*	-	-	
	8	-	-	-	-	-	-	0.1	*	-	-	
	<b>Total</b>	----	<b>1.5</b>	<b>0.9</b>	<b>49.5</b>	<b>56.9</b>	<b>48.5</b>	<b>26.5</b>	<b>3.8</b>	<b>10.1</b>	<b>84.0</b>	<b>81.3</b>
	51	1-2	-	-	-	*	*	*	*	*	*	*
3		-	-	*	*	*	*	0.1	0.2	0.2	0.1	
4		-	-	0.1	0.2	*	*	0.1	0.2	0.2	0.2	
5		*	*	0.2	0.3	*	*	*	0.1	0.1	0.1	
6		*	*	*	0.1	*	*	*	*	*	*	
7		*	*	-	-	*	*	*	*	-	-	
8		-	-	-	-	-	-	*	*	-	-	
<b>Total</b>		----	<b>*</b>	<b>*</b>	<b>0.3</b>	<b>0.7</b>	<b>0.1</b>	<b>0.1</b>	<b>0.2</b>	<b>0.6</b>	<b>0.4</b>	<b>0.4</b>
61		1-2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	*	-	-	
	4	-	-	-	*	-	-	-	*	-	-	
	5	-	-	-	-	-	-	-	*	-	-	
	6	-	-	-	-	-	-	*	*	-	-	
	7	-	-	-	-	-	-	-	*	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	<b>Total</b>	----	<b>-</b>	<b>-</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>-</b>	<b>*</b>	<b>*</b>	<b>-</b>	<b>-</b>
	71	1-2	-	-	-	-	-	-	-	-	-	-
3		-	-	-	-	-	-	-	-	-	-	
4		-	-	-	-	-	-	-	*	-	-	
5		-	-	-	-	-	-	-	-	-	-	
6		-	-	-	-	-	-	-	*	-	-	
7		-	-	-	-	-	-	-	-	-	-	
8		-	-	-	-	-	-	-	-	-	-	
<b>Total</b>		----	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>-</b>	
12 & 22		1-2	1.4	1.3	-	-	-	*	2.9	2.6	-	-
	3	0.6	0.7	-	*	*	*	1.1	1.4	-	*	
	4	*	*	-	*	-	*	0.2	0.2	-	-	
	5	-	-	-	-	-	-	*	*	-	-	
	6	-	-	-	-	-	-	*	*	-	-	
	7	-	-	-	-	-	-	-	-	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	<b>Total</b>	----	<b>2.0</b>	<b>2.0</b>	<b>-</b>	<b>*</b>	<b>*</b>	<b>0.1</b>	<b>4.3</b>	<b>4.3</b>	<b>-</b>	<b>*</b>
	32	1-2	0.5	0.2	-	*	0.1	0.3	0.1	0.2	-	*
3		0.7	0.4	0.1	0.3	0.3	1.0	0.3	1.1	0.1	0.3	
4		0.4	0.2	0.2	0.2	0.1	0.2	0.3	0.7	*	0.3	
5		0.1	0.1	0.1	0.1	*	*	0.2	0.2	*	0.2	
6		-	*	-	-	-	-	0.1	*	-	*	
7		-	-	-	-	-	-	*	*	-	-	
8		-	-	-	-	-	-	*	*	-	-	
<b>Total</b>		----	<b>1.8</b>	<b>0.9</b>	<b>0.4</b>	<b>0.6</b>	<b>0.5</b>	<b>1.5</b>	<b>1.0</b>	<b>2.3</b>	<b>0.2</b>	<b>0.7</b>
42		1-2	*	*	*	*	0.1	*	*	0.1	*	*
	3	*	*	0.4	0.5	0.2	0.3	0.4	0.9	1.2	1.8	
	4	*	*	0.8	1.0	0.1	0.2	0.4	1.1	2.4	2.3	
	5	0.1	0.1	0.5	0.4	*	*	0.1	0.4	0.8	0.6	
	6	*	*	0.1	0.1	-	*	*	0.2	*	*	
	7	*	*	-	-	-	-	*	*	-	-	
	8	-	*	-	-	-	-	*	*	-	-	
	<b>Total</b>	----	<b>0.1</b>	<b>0.1</b>	<b>1.7</b>	<b>2.0</b>	<b>0.4</b>	<b>0.5</b>	<b>1.0</b>	<b>2.8</b>	<b>4.3</b>	<b>4.6</b>

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Nov 19, 2020**

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA		
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	
Color 52	1-2	-	-	-	-	-	*	*	*	*	-	*
	3	-	-	*	*	*	*	0.2	0.4	*	*	
	4	-	-	0.2	0.1	*	*	0.2	0.4	0.1	0.1	
	5	-	-	0.1	0.1	-	-	0.1	0.3	*	*	
	6	-	-	*	*	-	*	*	0.1	-	-	
	7	-	-	-	-	-	-	*	*	-	-	
	8	-	-	-	-	-	-	*	*	-	-	
	<b>Total</b>	----	-	-	<b>0.4</b>	<b>0.2</b>	<b>*</b>	<b>*</b>	<b>0.5</b>	<b>1.2</b>	<b>0.2</b>	<b>0.1</b>
62	1-2	-	-	-	-	-	-	-	-	-	-	
	3	-	-	-	-	-	-	-	*	-	-	
	4	-	-	-	-	-	-	*	*	-	-	
	5	-	-	-	-	-	-	*	*	-	-	
	6	-	-	-	-	-	-	-	*	-	-	
	7	-	-	-	-	-	-	-	*	-	-	
	8	-	-	-	-	-	-	-	*	-	-	
	<b>Total</b>	----	-	-	-	-	-	-	<b>*</b>	<b>*</b>	-	-
13 & 23	1-2	0.2	0.2	-	-	-	*	0.6	0.2	-	-	
	3	0.2	0.2	-	-	*	*	0.2	0.1	-	-	
	4	*	*	-	-	-	-	*	*	-	-	
	5	-	*	-	-	-	-	*	*	-	-	
	6	-	-	-	-	-	-	-	*	-	-	
	7	-	-	-	-	-	-	-	-	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	<b>Total</b>	----	<b>0.4</b>	<b>0.4</b>	-	-	<b>*</b>	<b>*</b>	<b>0.8</b>	<b>0.4</b>	-	-
33	1-2	0.3	0.1	-	-	*	*	0.1	*	-	-	
	3	0.4	0.2	-	-	0.1	*	0.1	0.1	-	-	
	4	0.1	0.1	-	*	*	*	*	0.1	-	-	
	5	*	*	-	*	-	*	*	*	-	-	
	6	*	*	-	-	-	-	*	*	-	-	
	7	-	-	-	-	-	-	*	*	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	<b>Total</b>	----	<b>0.9</b>	<b>0.5</b>	-	<b>*</b>	<b>0.1</b>	<b>*</b>	<b>0.2</b>	<b>0.2</b>	-	-
43	1-2	-	-	-	-	*	*	*	*	-	-	
	3	*	*	-	*	*	*	0.1	0.1	0.1	0.1	
	4	0.1	*	*	*	*	*	0.1	0.2	0.1	*	
	5	*	*	0.1	*	-	*	*	0.1	*	*	
	6	*	*	*	*	-	-	*	*	-	-	
	7	-	*	-	-	-	-	*	*	-	-	
	8	-	*	-	-	-	-	*	*	-	-	
	<b>Total</b>	----	<b>0.1</b>	<b>0.1</b>	<b>0.1</b>	<b>0.1</b>	<b>0.1</b>	<b>*</b>	<b>0.2</b>	<b>0.5</b>	<b>0.1</b>	<b>0.1</b>
53	1-2	-	*	-	-	-	*	*	*	-	-	
	3	-	-	-	-	-	*	*	0.1	-	-	
	4	-	-	*	*	-	*	0.1	0.2	-	-	
	5	-	*	*	*	-	-	*	0.2	-	-	
	6	-	*	*	*	-	-	*	0.1	-	-	
	7	-	*	-	-	-	-	*	*	-	-	
	8	-	*	-	-	-	-	-	*	-	-	
	<b>Total</b>	----	-	<b>*</b>	<b>0.1</b>	<b>0.1</b>	-	<b>*</b>	<b>0.1</b>	<b>0.6</b>	-	-
63	1-2	-	-	-	-	-	-	-	*	-	-	
	3	-	-	-	-	-	-	*	*	-	-	
	4	-	-	-	*	-	-	*	*	-	-	
	5	-	-	-	-	-	-	-	*	-	*	
	6	-	-	-	-	-	-	*	*	-	-	
	7	-	-	-	-	-	-	*	*	-	-	
	8	-	*	-	-	-	-	-	*	-	-	
	<b>Total</b>	----	-	<b>*</b>	-	<b>*</b>	-	-	<b>*</b>	<b>*</b>	-	<b>*</b>
24 - 54	1-8	0.2	0.2	*	*	-	*	0.2	0.1	-	-	
25 - 35	1-8	-	*	-	-	-	-	*	*	-	-	
81 - 85	1-8	-	*	-	-	-	-	*	*	-	-	
STAPLE												
28 & Shorter		-	*	-	-	-	-	*	*	-	-	
29		-	*	-	-	-	-	*	*	-	-	
30		*	*	-	-	-	-	0.1	0.1	-	-	
31		0.3	0.4	-	-	-	-	0.4	0.3	-	-	
32		0.7	1.3	-	-	-	-	1.8	1.2	-	-	
33		1.6	2.9	0.1	*	*	*	5.6	3.5	-	-	
34		5.8	5.8	1.0	0.4	0.2	0.1	13.0	8.3	*	*	
35		9.8	7.3	3.3	2.7	2.7	3.1	19.1	15.2	0.8	0.6	
36		12.5	11.4	7.6	7.8	15.2	16.1	22.9	24.0	4.2	3.0	
37		25.7	25.9	17.7	22.0	41.1	39.0	23.3	28.9	24.7	20.4	
38		24.2	24.6	31.3	30.2	24.6	25.1	9.1	12.8	29.3	29.1	
39		14.1	15.0	28.4	27.3	13.6	13.9	3.4	4.5	20.6	23.3	
40 & Longer		5.3	5.4	10.5	9.5	2.6	2.6	1.3	1.3	20.4	23.6	
<b>Average Staple</b>		<b>37.08</b>	<b>37.07</b>	<b>38.03</b>	<b>38.00</b>	<b>37.38</b>	<b>37.38</b>	<b>35.85</b>	<b>36.25</b>	<b>38.30</b>	<b>38.47</b>	
<b>Average Length</b>		<b>1.16</b>	<b>1.16</b>	<b>1.19</b>	<b>1.19</b>	<b>1.17</b>	<b>1.17</b>	<b>1.12</b>	<b>1.13</b>	<b>1.20</b>	<b>1.20</b>	

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Nov 19, 2020**

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	0.8	0.8	1.0	0.7	*	*	-	*	1.7	1.4	0.7	0.7
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	*	*	*	*	*	1.4	0.5	*	*	*	*
Grass - Level 2	-	-	-	*	-	-	-	-	-	-	-	-
Prep - Level 1	*	*	*	*	*	*	-	-	-	*	*	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	26.1	14.3	*	*	4.2	3.2	*	0.3	45.9	36.3	36.4	23.1
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	*	*	-	-	-	-	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	*	*	*	*	*	*	-	-	-	*	*	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	0.1	-	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
<b>STRENGTH 1/</b>												
22 & Below	-	*	-	-	-	-	-	-	-	-	*	*
23	*	*	*	*	-	*	-	-	*	*	*	*
24	*	0.1	*	*	*	*	-	*	-	*	*	*
25	0.1	0.2	*	*	*	0.2	-	*	0.1	0.1	0.1	0.2
26	0.4	0.4	0.1	0.1	0.3	0.7	*	0.2	0.3	0.9	0.4	0.9
27	2.0	1.4	0.6	0.4	1.6	3.5	0.3	0.8	1.2	2.1	2.2	3.9
28	6.6	6.3	3.5	2.2	4.4	12.9	1.2	1.7	5.0	6.9	7.6	11.3
29	21.2	22.0	14.2	10.5	13.0	18.9	2.9	8.5	22.9	25.4	18.6	22.4
30	32.1	32.0	31.5	26.4	23.0	22.2	5.6	14.8	33.5	34.4	28.7	27.5
31	21.3	22.2	29.6	30.8	24.7	19.8	13.1	16.6	24.6	19.3	23.0	18.9
32	10.0	9.7	13.4	17.7	17.1	11.3	17.9	15.9	9.4	7.2	11.3	8.9
33	4.1	3.8	5.4	7.6	8.1	6.1	13.7	7.3	2.2	2.9	5.1	3.8
34	1.7	1.4	1.6	3.4	5.1	3.0	6.0	4.2	0.6	0.7	2.0	1.5
35	0.4	0.4	0.2	0.8	1.9	1.0	9.4	10.3	0.2	0.1	0.7	0.5
36	0.1	0.1	*	0.1	0.5	0.3	14.1	11.5	0.1	*	0.2	0.1
37	*	*	*	*	0.2	0.1	11.3	6.2	-	*	*	*
38	*	*	-	*	*	*	3.3	1.4	-	-	*	*
39	*	*	-	-	*	*	0.5	0.2	-	-	*	*
40 & Above	-	-	-	-	*	*	0.6	0.3	-	-	-	-
<b>Average</b>	<b>30.65</b>	<b>30.63</b>	<b>31.01</b>	<b>31.36</b>	<b>31.34</b>	<b>30.66</b>	<b>34.01</b>	<b>32.98</b>	<b>30.63</b>	<b>30.42</b>	<b>30.76</b>	<b>30.41</b>
<b>Mike</b>												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5	-	-	-	-	-	-	-	-	-	-	-	-
2.6	-	*	-	-	-	-	-	-	-	-	*	*
2.7	-	-	-	-	-	*	0.1	*	-	-	*	*
2.8	*	*	-	-	*	*	0.1	*	-	-	*	*
2.9	*	*	-	-	*	*	-	*	-	-	*	*
3.0	*	*	*	*	*	*	0.2	0.1	-	-	*	*
3.1	*	*	*	*	0.1	*	0.1	*	*	*	*	*
3.2	0.1	*	*	*	0.2	0.1	0.1	*	0.1	*	*	*
3.3	0.2	0.1	*	*	0.2	0.1	0.2	0.1	0.1	*	0.1	*
3.4	0.5	0.2	*	0.1	0.3	0.1	0.4	0.4	0.3	0.1	0.2	0.1
3.5	0.6	0.3	0.2	0.3	0.3	0.1	1.4	0.9	0.9	0.4	0.3	0.1
3.6	1.0	0.7	0.7	0.6	0.3	0.1	1.7	1.1	1.7	1.3	0.4	0.2
3.7	1.5	1.2	1.1	1.0	0.4	0.3	3.2	2.3	1.7	1.7	0.6	0.5
3.8	2.8	2.1	2.1	1.8	0.4	0.3	2.4	3.7	3.1	2.1	1.0	0.8
3.9	2.9	2.7	3.9	3.1	0.6	0.5	3.9	6.1	3.4	2.7	1.7	1.5
4.0	4.3	4.1	5.6	4.8	1.2	0.9	2.0	6.6	7.3	5.8	2.9	2.8
4.1	5.2	5.3	8.4	7.5	2.9	1.9	2.6	6.5	11.2	8.8	4.8	4.7
4.2	7.2	6.9	11.3	11.0	3.3	3.3	4.7	7.7	11.7	10.9	7.1	7.5
4.3	9.5	8.9	14.3	13.5	4.7	4.9	9.6	8.5	14.3	12.9	10.2	10.7
4.4	10.3	10.8	14.0	14.9	7.2	8.2	12.7	10.9	13.9	15.1	12.2	13.6
4.5	12.1	12.1	13.4	14.9	11.2	11.4	17.0	11.9	11.5	13.3	13.6	14.3
4.6	12.5	12.3	11.2	11.4	12.5	12.8	15.3	10.0	10.8	11.3	13.2	13.4
4.7	9.4	10.7	6.6	7.2	9.3	13.6	7.8	7.6	3.9	5.4	11.7	10.8
4.8	7.3	8.1	3.5	4.1	10.8	13.1	4.7	5.5	2.4	2.9	9.1	8.2
4.9	5.8	5.7	1.8	2.1	10.4	11.2	4.8	4.9	1.2	2.1	5.5	5.2
5.0	3.5	3.6	0.8	0.9	9.1	7.1	4.4	3.0	0.3	1.9	2.9	3.1
5.1	1.6	2.1	0.5	0.4	7.8	5.1	0.6	1.4	0.2	0.9	1.4	1.4
5.2	1.0	1.1	0.3	0.2	4.7	2.8	*	0.7	0.1	0.2	0.4	0.5
5.3	0.3	0.5	0.1	0.1	0.9	1.1	*	0.1	*	0.1	0.3	0.2
5.4	0.1	0.3	*	*	0.8	0.6	-	*	*	*	0.2	0.2
5.5 & Above	0.1	0.1	*	*	0.3	0.2	-	*	-	-	0.2	0.1
<b>Average</b>	<b>4.45</b>	<b>4.48</b>	<b>4.36</b>	<b>4.38</b>	<b>4.68</b>	<b>4.67</b>	<b>4.41</b>	<b>4.37</b>	<b>4.29</b>	<b>4.36</b>	<b>4.50</b>	<b>4.50</b>

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

\* Less than 0.05 percent.



**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Nov 19, 2020**

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	13.4	13.9	2.1	0.6	0.4	0.1	0.6	0.5	0.3	0.2	-	0.2
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	*	*	*	*	*	0.1	0.1	*	*	-	*
Grass - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
Prep - Level 1	-	-	-	*	*	*	*	*	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	-	*	*	0.1	*	*	*	0.1	0.1
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	*	-	-	-	*	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	*	*	*	*	-	-	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	-	*	*	*	*	*	*	*	*	-	-
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	*	*	-	-	-	-	-	-	-	-	-	-
23	0.6	0.3	-	-	-	-	-	-	-	-	-	-
24	1.9	1.0	-	-	-	*	*	*	*	*	-	-
25	4.0	2.5	-	*	*	*	*	*	0.1	*	-	-
26	3.0	3.6	*	*	*	*	0.2	0.2	0.4	0.2	*	*
27	14.4	11.9	0.2	0.1	0.2	0.1	1.6	1.1	1.8	1.3	1.6	0.8
28	32.0	26.0	2.4	0.9	1.5	0.8	6.3	4.0	6.4	4.6	17.9	10.3
29	22.7	22.9	11.4	6.6	14.0	6.6	15.5	14.5	18.3	13.9	23.3	24.0
30	13.0	16.4	32.7	26.8	35.1	27.1	29.0	29.8	28.4	25.8	15.8	29.3
31	5.0	9.4	28.1	29.7	32.5	37.3	26.1	27.8	23.9	26.0	18.9	20.6
32	2.5	4.6	12.1	15.1	11.0	18.4	13.1	13.2	13.4	15.5	21.0	13.6
33	0.4	1.0	6.0	10.5	3.9	6.5	5.3	6.0	5.4	7.2	1.2	1.1
34	0.4	0.3	4.1	6.8	1.3	2.4	2.4	2.6	1.4	3.6	0.1	0.1
35	*	*	2.7	2.8	0.3	0.6	0.5	0.8	0.6	1.5	-	*
36	-	*	0.2	0.6	0.1	0.1	*	0.1	0.1	0.3	*	*
37	-	-	0.2	0.1	*	*	*	*	*	*	*	*
38	-	-	*	*	*	*	-	*	-	*	-	-
39	-	-	-	-	-	-	-	-	-	-	-	-
40 & Above	-	-	-	-	-	-	-	-	-	-	-	-
<b>Average</b>	<b>28.79</b>	<b>29.21</b>	<b>31.30</b>	<b>31.73</b>	<b>31.02</b>	<b>31.44</b>	<b>30.91</b>	<b>31.05</b>	<b>30.82</b>	<b>31.19</b>	<b>30.49</b>	<b>30.49</b>
Mike												
2.4 & Below	0.1	*	-	-	-	-	-	-	-	-	-	-
2.5	4.2	3.4	-	-	-	-	-	-	-	-	-	-
2.6	2.8	2.2	-	-	-	-	-	-	-	*	-	-
2.7	3.8	2.8	-	-	-	-	-	-	*	*	-	-
2.8	2.6	3.0	-	-	-	-	-	-	*	*	-	-
2.9	6.5	5.4	-	*	-	-	-	-	*	*	-	-
3.0	6.8	7.3	*	*	*	*	-	*	*	*	0.6	0.2
3.1	5.1	6.5	*	*	*	*	*	*	*	*	0.5	0.2
3.2	6.5	6.5	-	*	*	*	*	*	0.1	0.1	-	-
3.3	6.6	7.3	-	*	0.1	*	*	*	0.2	0.3	-	-
3.4	8.0	9.2	-	*	0.2	0.1	*	*	0.6	0.6	-	-
3.5	7.5	8.7	*	0.1	0.4	0.3	*	*	0.7	0.6	1.1	0.7
3.6	6.0	7.9	*	0.2	1.3	0.6	*	*	1.2	1.1	3.1	1.9
3.7	5.2	6.8	0.1	0.2	1.8	1.1	0.1	0.1	1.5	1.7	2.7	1.6
3.8	6.4	5.6	0.2	0.4	3.2	2.1	0.2	0.2	3.1	3.0	3.8	1.9
3.9	4.2	4.5	0.7	1.1	5.5	3.7	0.3	0.3	4.4	4.9	2.9	3.0
4.0	3.4	2.6	1.8	1.8	8.9	5.8	0.4	0.8	6.9	6.7	5.0	5.2
4.1	2.2	3.2	2.2	2.8	10.6	7.8	1.3	1.7	9.3	8.4	6.1	6.9
4.2	5.1	3.4	3.9	4.9	11.9	9.9	2.7	3.2	11.3	9.7	6.4	7.4
4.3	4.6	2.3	7.3	8.1	10.7	11.1	4.8	5.4	12.5	10.7	9.9	8.9
4.4	2.0	1.0	11.2	11.8	11.9	12.7	7.7	8.7	11.8	11.5	8.1	11.9
4.5	0.3	0.2	13.3	13.6	10.9	12.4	11.6	13.0	11.7	11.6	10.1	10.0
4.6	-	*	20.9	16.8	7.3	9.9	16.6	15.9	9.7	10.2	12.7	11.5
4.7	*	*	14.7	15.2	5.4	7.8	16.5	16.9	6.9	8.5	9.2	8.1
4.8	-	-	12.4	10.8	4.3	5.5	15.7	14.2	4.3	5.6	5.2	8.4
4.9	-	-	6.9	7.0	3.0	3.9	10.2	9.8	2.0	3.1	6.8	7.3
5.0	-	-	2.4	3.5	1.5	2.5	6.1	5.3	0.9	1.2	1.7	1.9
5.1	-	-	1.0	1.1	0.7	1.5	3.6	2.8	0.4	0.3	2.3	1.7
5.2	-	-	0.3	0.3	0.4	0.9	1.6	1.2	0.1	0.1	1.7	1.2
5.3	-	-	0.2	0.1	0.1	0.2	0.3	0.3	-	*	0.1	*
5.4	-	-	0.2	0.1	*	0.1	0.1	0.1	*	*	-	-
5.5 & Above	-	-	0.1	*	-	*	*	*	-	*	-	-
<b>Average</b>	<b>3.43</b>	<b>3.41</b>	<b>4.58</b>	<b>4.56</b>	<b>4.31</b>	<b>4.41</b>	<b>4.67</b>	<b>4.64</b>	<b>4.32</b>	<b>4.34</b>	<b>4.39</b>	<b>4.43</b>

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Nov 19, 2020**

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	5.0	3.6	1.5	1.2	0.1	*	5.1	3.5	0.6	0.5
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	*	*	0.2	*	*	0.2	0.2	0.1	*
Grass - Level 2	-	-	-	-	-	-	-	*	-	-
Prep - Level 1	*	*	-	*	-	-	*	*	*	*
Prep - Level 2	-	-	-	-	-	-	-	*	-	-
Seed Coat - Level 1	-	*	-	*	-	-	0.1	*	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	-	-	*	*	*	0.1	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	-	-	-	*	*	-	-
Other - Level 2	-	-	-	-	-	-	-	*	-	-
Plastic - Level 1	*	*	*	*	*	*	*	*	*	*
Plastic - Level 2	-	*	-	-	-	-	-	*	-	-
<b>STRENGTH 1/</b>										
22 & Below	*	*	-	-	-	-	*	*	-	-
23	*	*	-	-	-	-	0.2	0.1	-	-
24	0.1	0.1	-	-	*	*	0.4	0.3	-	-
25	0.3	0.5	*	*	*	*	0.9	0.9	*	*
26	0.8	1.2	0.3	0.2	0.1	*	2.6	2.1	0.2	0.1
27	2.7	3.3	2.2	1.3	1.0	0.4	6.6	4.8	1.7	1.2
28	9.3	7.6	9.5	6.9	6.9	3.9	13.0	9.9	7.5	5.7
29	16.1	14.2	26.8	22.4	27.4	19.6	18.1	16.8	22.3	18.0
30	20.8	17.8	32.0	34.2	38.8	35.8	19.9	20.6	27.2	26.6
31	17.8	18.9	18.5	21.2	19.8	26.2	17.4	18.2	20.7	25.5
32	15.2	16.8	7.1	9.2	4.4	10.1	11.5	12.8	13.1	14.0
33	9.8	11.5	2.1	3.2	1.5	3.0	5.9	8.2	5.2	6.5
34	4.5	5.5	1.0	1.1	0.2	0.8	2.4	3.5	1.8	1.8
35	1.6	1.7	0.4	0.3	*	0.1	0.8	1.2	0.3	0.6
36	0.7	0.6	*	0.1	*	*	0.2	0.3	0.1	0.1
37	0.1	0.1	-	-	-	*	0.1	0.1	*	*
38	*	*	-	-	-	-	*	*	-	-
39	-	*	-	-	-	-	*	*	-	-
40 & Above	-	-	-	-	-	-	-	*	-	-
<b>Average</b>	<b>31.04</b>	<b>31.19</b>	<b>30.36</b>	<b>30.59</b>	<b>30.34</b>	<b>30.75</b>	<b>30.36</b>	<b>30.70</b>	<b>30.73</b>	<b>30.94</b>
<b>Mike</b>										
2.4 & Below	*	*	-	-	-	-	0.1	*	-	-
2.5	*	*	-	-	-	-	0.6	0.2	-	-
2.6	*	*	-	-	-	-	1.0	0.3	-	-
2.7	*	*	-	*	-	-	1.1	0.3	-	-
2.8	0.1	0.1	-	*	-	-	1.3	0.4	-	-
2.9	0.3	0.2	-	*	-	-	1.5	0.5	-	-
3.0	1.1	0.6	-	*	-	-	1.8	0.7	-	-
3.1	1.0	0.7	-	*	-	-	2.3	0.9	-	*
3.2	1.0	1.3	-	*	*	*	2.7	1.0	0.1	0.1
3.3	2.5	2.0	*	*	0.2	*	3.2	1.3	0.2	0.1
3.4	3.5	2.7	0.2	0.1	0.3	0.1	3.5	1.6	0.5	0.3
3.5	3.8	3.6	0.5	0.3	0.6	0.2	3.9	2.0	0.5	0.4
3.6	4.4	4.5	0.6	0.5	0.8	0.3	4.4	2.6	0.6	0.5
3.7	5.0	4.7	1.0	1.1	2.0	0.8	5.0	3.5	1.0	0.8
3.8	6.1	6.1	2.6	2.4	2.7	1.3	5.7	4.6	1.9	1.9
3.9	7.6	7.3	5.8	4.7	4.5	1.8	6.6	5.8	3.2	2.8
4.0	9.7	9.6	8.2	6.9	6.0	2.9	6.9	7.1	5.3	6.2
4.1	9.9	11.0	9.8	8.5	7.7	4.3	7.1	8.2	6.9	6.4
4.2	9.8	11.0	12.4	10.8	8.6	6.2	6.9	9.1	11.7	10.9
4.3	8.6	9.2	13.8	12.8	9.7	8.2	7.1	9.6	13.0	13.4
4.4	7.3	7.8	13.6	13.8	10.8	10.3	6.8	9.4	14.2	14.9
4.5	6.4	6.6	11.1	11.7	10.2	11.6	5.8	8.8	11.7	13.0
4.6	4.7	4.8	8.1	9.7	9.7	11.9	4.8	7.6	9.1	9.0
4.7	3.0	2.7	4.6	6.7	8.2	11.5	3.8	5.7	8.4	8.6
4.8	2.0	1.6	3.0	4.5	7.3	10.7	2.5	3.9	6.0	6.2
4.9	1.2	0.9	2.4	2.8	5.0	7.7	1.6	2.5	3.2	2.8
5.0	0.7	0.5	1.7	1.7	3.0	4.9	0.9	1.4	1.2	0.9
5.1	0.1	0.3	0.5	0.6	1.6	2.9	0.4	0.7	0.6	0.5
5.2	*	0.1	0.2	0.2	0.7	1.5	0.2	0.3	0.4	0.3
5.3	0.1	*	*	0.1	0.3	0.5	0.1	0.1	0.2	0.1
5.4	*	*	-	*	0.1	0.1	*	*	-	-
5.5 & Above	*	*	-	*	*	*	*	*	-	-
<b>Average</b>	<b>4.06</b>	<b>4.08</b>	<b>4.32</b>	<b>4.36</b>	<b>4.40</b>	<b>4.55</b>	<b>3.96</b>	<b>4.19</b>	<b>4.38</b>	<b>4.38</b>

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).  
\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE  
For The Week Ending Nov 19, 2020**

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	-	*	-	-	-	-	-	-	-	-	*	*
2.7 - 2.9	*	*	-	-	*	*	0.1	0.1	-	-	*	*
3.0 - 3.2	0.2	0.1	*	*	0.4	0.1	0.4	0.1	0.1	*	0.1	*
3.3 - 3.4	0.7	0.3	0.1	0.1	0.5	0.1	0.7	0.5	0.5	0.2	0.3	0.1
3.5 - 3.6	1.6	1.0	0.8	0.9	0.6	0.2	3.1	1.9	2.6	1.7	0.7	0.3
3.7 - 4.2	23.9	22.3	32.5	29.3	8.9	7.3	18.9	32.9	38.4	32.0	18.1	17.9
4.3 - 4.9	67.0	68.6	64.8	68.2	66.1	75.2	71.9	59.2	57.8	63.0	75.4	76.2
5.0 - 5.2	6.1	6.8	1.6	1.5	21.6	15.1	4.9	5.1	0.6	3.0	4.7	5.0
5.3 & Above	0.5	0.9	0.2	0.1	2.1	2.0	*	0.2	*	0.1	0.7	0.5
<b>Average</b>	<b>4.45</b>	<b>4.48</b>	<b>4.36</b>	<b>4.38</b>	<b>4.68</b>	<b>4.67</b>	<b>4.41</b>	<b>4.37</b>	<b>4.29</b>	<b>4.36</b>	<b>4.50</b>	<b>4.50</b>
Leaf												
1 - 2	2.9	3.0	1.8	2.9	86.4	89.8	69.4	76.6	1.3	1.7	2.5	2.6
3	39.7	38.0	32.5	36.2	11.3	8.8	28.1	20.5	24.5	29.4	39.5	38.4
4	45.6	45.7	51.7	47.9	1.9	1.2	2.5	2.8	57.3	51.9	45.6	45.8
5	10.9	12.1	13.3	12.3	0.3	0.2	*	0.1	15.6	15.6	11.0	11.7
6	1.0	1.2	0.7	0.7	0.1	*	-	-	1.2	1.3	1.3	1.3
7	*	0.1	*	*	*	*	-	-	0.1	0.1	0.1	0.1
8	-	*	*	*	*	*	-	-	-	-	-	*
<b>Average</b>	<b>3.67</b>	<b>3.71</b>	<b>3.79</b>	<b>3.72</b>	<b>1.79</b>	<b>1.67</b>	<b>2.16</b>	<b>2.02</b>	<b>3.91</b>	<b>3.86</b>	<b>3.69</b>	<b>3.71</b>
HVI Trash 1/												
00	-	-	-	-	*	*	*	0.1	-	-	*	*
01	0.1	0.2	0.1	0.1	56.7	64.1	30.7	40.5	*	0.1	0.2	0.2
02	4.0	3.9	2.1	3.4	31.4	27.5	42.3	37.9	2.0	2.8	4.2	4.3
03	15.9	15.4	10.8	13.0	7.4	5.5	18.7	13.6	9.1	12.1	16.7	16.6
04	25.2	24.5	21.2	21.7	2.6	1.7	5.6	4.7	20.7	22.1	25.1	25.2
05	23.5	23.1	24.1	23.0	1.0	0.7	1.9	2.0	26.2	24.5	22.6	22.6
06	15.4	15.7	19.0	17.9	0.3	0.2	0.6	0.8	20.5	18.4	15.0	15.0
07	8.4	8.9	11.6	10.8	0.2	0.1	0.1	0.3	11.5	10.5	8.4	8.3
08	4.1	4.5	6.2	5.6	0.1	0.1	0.1	0.1	5.5	5.0	4.2	4.2
09	1.9	2.1	3.0	2.7	0.1	0.1	*	*	2.7	2.5	2.0	2.0
10	0.8	0.9	1.2	1.1	0.1	*	-	*	1.1	1.1	0.9	0.9
11	0.4	0.4	0.5	0.5	*	*	-	-	0.5	0.5	0.4	0.4
12	0.2	0.2	0.2	0.2	*	*	-	*	0.2	0.2	0.2	0.2
13	0.1	0.1	0.1	0.1	*	*	-	*	*	0.1	0.1	0.1
14	*	*	*	*	*	*	-	-	*	*	*	*
15	*	*	*	*	-	*	-	-	*	*	*	*
16	*	*	*	*	-	-	-	-	*	*	*	*
17	*	*	*	*	-	-	-	-	-	-	*	*
18 & Above	*	*	*	*	*	*	-	-	-	*	*	*
<b>Average</b>	<b>0.49</b>	<b>0.50</b>	<b>0.53</b>	<b>0.52</b>	<b>0.16</b>	<b>0.15</b>	<b>0.21</b>	<b>0.19</b>	<b>0.54</b>	<b>0.52</b>	<b>0.49</b>	<b>0.49</b>
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	-	-	-	-	-	-	-	-	-	-	*	*
76	*	*	*	*	*	*	-	*	-	0.1	*	*
77	0.2	0.3	*	*	0.3	0.3	0.2	0.1	0.1	0.2	0.2	0.3
78	1.1	1.4	0.2	0.3	2.3	2.4	0.3	0.7	0.6	1.2	1.4	1.9
79	6.2	6.5	1.6	1.6	14.8	12.2	7.9	8.8	4.1	7.0	6.4	8.2
80	25.3	25.5	11.2	10.8	32.2	30.6	12.6	26.1	30.8	36.6	18.4	23.6
81	40.7	39.8	34.4	34.8	34.4	38.1	26.6	30.9	48.1	41.5	34.3	35.3
82	21.1	21.4	36.4	36.6	14.3	14.8	17.7	10.4	14.1	11.6	27.8	22.7
83	4.9	4.6	14.3	13.8	1.5	1.4	27.7	16.2	2.1	1.6	9.4	6.8
84	0.5	0.5	1.7	1.9	0.1	0.2	6.7	6.5	0.2	0.1	1.7	1.1
85 & Above	*	*	0.1	0.1	*	*	0.3	0.3	*	*	0.2	0.1
<b>Average</b>	<b>81.36</b>	<b>81.34</b>	<b>82.00</b>	<b>82.00</b>	<b>80.93</b>	<b>81.00</b>	<b>82.09</b>	<b>81.61</b>	<b>81.23</b>	<b>81.05</b>	<b>81.62</b>	<b>81.38</b>
Tenderable 3/	<b>62.7</b>	<b>69.9</b>	<b>95.4</b>	<b>96.1</b>	<b>72.8</b>	<b>80.4</b>	<b>92.2</b>	<b>93.1</b>	<b>48.4</b>	<b>52.5</b>	<b>55.7</b>	<b>62.1</b>
<b>SAMPLES CLASSED</b>	<b>63,144</b>	<b>288,413</b>	<b>140,870</b>	<b>744,427</b>	<b>25,535</b>	<b>102,094</b>	<b>15,759</b>	<b>54,933</b>	<b>10,620</b>	<b>26,560</b>	<b>173,759</b>	<b>616,521</b>

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. \* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE  
For The Week Ending Nov 19, 2020**

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	0.1	*	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	7.0	5.6	-	-	-	-	-	-	-	*	-	-
2.7 - 2.9	12.9	11.2	-	*	-	-	-	-	*	*	-	-
3.0 - 3.2	18.4	20.3	*	*	0.1	*	*	*	0.2	0.1	1.1	0.5
3.3 - 3.4	14.6	16.5	-	0.1	0.3	0.2	*	*	0.9	0.9	-	-
3.5 - 3.6	13.6	16.7	0.1	0.3	1.7	0.9	*	*	1.9	1.7	4.3	2.6
3.7 - 4.2	26.6	26.2	8.9	11.3	41.8	30.5	4.9	6.2	36.6	34.4	26.9	26.0
4.3 - 4.9	6.9	3.5	86.8	83.2	53.5	63.4	83.3	83.9	59.0	61.3	62.0	66.1
5.0 - 5.2	-	-	3.7	4.9	2.6	4.8	11.3	9.4	1.4	1.6	5.7	4.8
5.3 & Above	-	-	0.5	0.2	0.1	0.3	0.4	0.5	*	*	0.1	*
<b>Average</b>	<b>3.43</b>	<b>3.41</b>	<b>4.58</b>	<b>4.56</b>	<b>4.31</b>	<b>4.41</b>	<b>4.67</b>	<b>4.64</b>	<b>4.32</b>	<b>4.34</b>	<b>4.39</b>	<b>4.43</b>
Leaf												
1 - 2	42.1	35.4	2.1	3.9	4.5	11.5	3.6	4.0	5.7	6.6	97.4	96.4
3	32.6	36.8	37.3	39.6	44.1	47.2	34.8	36.1	54.5	55.1	2.5	3.5
4	17.9	19.9	48.8	47.3	44.2	35.5	47.3	45.9	36.0	34.0	*	*
5	5.6	5.3	10.8	8.8	7.0	5.6	13.4	13.2	3.7	4.1	*	*
6	1.3	1.7	1.0	0.4	0.2	0.2	0.9	0.9	0.1	0.2	-	-
7	0.2	0.7	0.1	*	*	*	*	*	-	-	-	-
8	0.2	0.3	-	-	-	-	-	-	-	-	-	-
<b>Average</b>	<b>2.84</b>	<b>2.97</b>	<b>3.71</b>	<b>3.62</b>	<b>3.54</b>	<b>3.35</b>	<b>3.73</b>	<b>3.71</b>	<b>3.38</b>	<b>3.36</b>	<b>1.51</b>	<b>1.56</b>
HVI Trash 1/												
00	-	*	-	-	-	-	-	-	-	-	*	*
01	19.4	14.7	*	0.3	0.1	1.0	0.2	0.2	0.2	0.4	70.5	65.9
02	25.3	22.9	2.9	4.6	5.1	11.1	4.0	4.4	7.4	8.3	27.1	30.1
03	16.3	19.0	14.4	15.2	16.4	20.4	12.6	13.3	24.0	24.5	2.1	3.4
04	12.0	14.4	23.6	24.1	23.8	22.6	19.9	20.4	28.9	28.4	0.2	0.4
05	9.0	10.4	23.8	23.8	23.2	19.6	21.7	21.4	21.7	20.3	0.1	0.1
06	6.9	7.2	17.1	16.6	16.2	13.2	17.5	17.0	11.1	10.8	*	*
07	3.8	3.9	9.9	8.9	9.0	7.1	11.8	11.2	4.5	4.7	-	-
08	2.1	2.3	4.7	3.9	3.9	3.1	6.7	6.3	1.5	1.8	-	-
09	1.9	1.6	2.0	1.6	1.6	1.2	3.3	3.2	0.5	0.6	-	-
10	1.1	1.1	0.8	0.6	0.6	0.4	1.5	1.5	0.2	0.2	*	*
11	0.8	0.8	0.3	0.2	0.2	0.1	0.6	0.7	*	0.1	-	-
12	0.5	0.6	0.1	0.1	0.1	*	0.3	0.3	*	*	-	-
13	0.4	0.4	0.1	*	*	*	0.1	0.1	*	*	-	-
14	0.2	0.3	*	*	*	*	*	*	*	*	-	-
15	0.1	0.2	*	*	*	*	*	*	*	*	-	-
16	0.1	0.1	*	*	*	*	*	*	-	*	-	-
17	0.1	0.1	*	*	*	*	*	*	-	-	-	-
18 & Above	0.1	0.1	*	*	*	*	*	*	-	-	-	-
<b>Average</b>	<b>0.35</b>	<b>0.37</b>	<b>0.51</b>	<b>0.49</b>	<b>0.48</b>	<b>0.44</b>	<b>0.53</b>	<b>0.52</b>	<b>0.43</b>	<b>0.43</b>	<b>0.13</b>	<b>0.14</b>
UNIFORMITY 2/												
74 & Below	*	*	-	-	-	-	-	-	-	-	-	-
75	0.1	0.1	-	-	-	-	-	-	-	-	-	-
76	2.1	1.1	-	-	-	*	-	-	-	*	-	*
77	10.0	6.9	-	-	*	*	0.1	0.1	0.1	0.1	-	*
78	10.8	16.1	0.1	0.1	0.1	0.1	0.6	0.5	0.5	0.5	*	0.6
79	34.1	31.7	1.3	0.7	0.5	0.4	3.0	2.5	3.3	3.0	3.3	5.3
80	26.5	29.1	11.7	6.4	5.4	5.0	14.8	12.9	13.2	13.3	22.5	18.1
81	15.5	14.2	41.9	33.5	27.9	27.4	38.4	39.6	36.2	34.0	40.1	43.8
82	0.9	0.8	36.5	45.8	43.6	42.4	34.5	35.8	33.8	34.1	32.4	29.4
83	*	*	7.6	12.1	19.9	21.2	7.6	7.7	11.0	12.8	1.7	2.7
84	-	*	0.8	1.2	2.6	3.1	1.1	0.9	1.7	2.0	-	-
85 & Above	-	*	0.1	0.1	0.2	0.3	0.1	0.1	0.2	0.2	-	*
<b>Average</b>	<b>79.68</b>	<b>79.72</b>	<b>81.85</b>	<b>82.11</b>	<b>82.31</b>	<b>82.35</b>	<b>81.75</b>	<b>81.80</b>	<b>81.85</b>	<b>81.91</b>	<b>81.53</b>	<b>81.48</b>
Tenderable 3/	36.5	37.8	86.2	87.7	96.1	94.0	83.6	86.6	94.5	94.2	92.9	93.8
<b>SAMPLES CLASSIFIED</b>	<b>9,938</b>	<b>19,938</b>	<b>36,250</b>	<b>272,921</b>	<b>68,486</b>	<b>278,769</b>	<b>127,566</b>	<b>725,205</b>	<b>60,830</b>	<b>148,369</b>	<b>2,581</b>	<b>6,071</b>

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. \* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Nov 19, 2020**

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	*	*	-	-	-	-	0.1	*	-	-
2.5 - 2.6	*	*	-	-	-	-	1.7	0.4	-	-
2.7 - 2.9	0.5	0.3	-	*	-	-	4.0	1.2	-	-
3.0 - 3.2	3.1	2.5	-	*	*	*	6.9	2.6	0.1	0.1
3.3 - 3.4	6.0	4.7	0.2	0.1	0.5	0.2	6.7	2.9	0.6	0.4
3.5 - 3.6	8.2	8.1	1.1	0.8	1.4	0.5	8.4	4.7	1.2	0.9
3.7 - 4.2	48.1	49.8	39.7	34.5	31.5	17.4	38.3	38.2	30.0	29.0
4.3 - 4.9	33.2	33.6	56.7	62.0	60.9	71.9	32.4	47.4	65.7	67.9
5.0 - 5.2	0.8	0.8	2.4	2.5	5.3	9.3	1.5	2.4	2.2	1.6
5.3 & Above	0.1	*	*	0.1	0.4	0.6	0.1	0.1	0.2	0.1
<b>Average</b>	<b>4.06</b>	<b>4.08</b>	<b>4.32</b>	<b>4.36</b>	<b>4.40</b>	<b>4.55</b>	<b>3.96</b>	<b>4.19</b>	<b>4.38</b>	<b>4.38</b>
Leaf										
1 - 2	63.1	77.5	2.6	3.1	15.6	24.4	67.7	47.0	6.0	8.2
3	30.5	18.3	38.6	39.5	55.4	55.8	22.5	35.4	58.6	59.5
4	4.8	3.2	45.1	45.5	26.2	18.3	7.1	13.9	32.4	29.5
5	1.1	0.8	12.8	11.1	2.7	1.5	1.9	3.0	3.0	2.8
6	0.4	0.2	0.8	0.7	0.1	*	0.6	0.7	*	0.1
7	*	*	-	-	*	*	0.2	0.1	-	-
8	-	*	-	-	-	-	0.1	*	-	-
<b>Average</b>	<b>2.22</b>	<b>1.90</b>	<b>3.70</b>	<b>3.67</b>	<b>3.16</b>	<b>2.96</b>	<b>2.17</b>	<b>2.58</b>	<b>3.32</b>	<b>3.27</b>
HVI Trash 1/										
00	0.1	0.4	-	-	-	*	0.2	0.2	-	-
01	30.1	47.0	0.1	0.1	1.4	3.9	41.4	24.5	0.2	0.4
02	32.4	29.7	3.5	3.9	14.7	20.6	29.5	23.6	7.8	9.2
03	21.0	12.7	15.3	15.6	25.5	28.2	13.3	19.3	24.4	25.2
04	9.3	5.5	23.8	24.5	24.7	22.8	7.2	14.2	29.4	28.8
05	3.5	2.2	23.4	23.5	16.7	13.3	3.8	8.6	20.4	19.6
06	1.6	1.1	16.2	15.9	9.4	6.6	2.0	4.6	10.4	9.8
07	0.7	0.5	9.3	8.9	4.5	2.9	1.1	2.4	4.8	4.4
08	0.5	0.4	4.7	4.3	2.0	1.1	0.6	1.2	1.6	1.6
09	0.3	0.2	2.2	1.9	0.7	0.4	0.4	0.7	0.6	0.6
10	0.2	0.1	0.8	0.8	0.3	0.1	0.2	0.4	0.2	0.2
11	0.1	0.1	0.3	0.3	0.1	*	0.1	0.2	0.1	0.1
12	0.1	*	0.2	0.1	*	*	0.1	0.1	*	*
13	*	*	0.1	*	*	*	0.1	0.1	*	*
14	*	*	*	*	*	*	*	*	-	-
15	-	*	*	*	*	*	*	*	-	-
16	*	*	-	-	-	*	*	*	-	-
17	*	*	-	-	-	-	*	*	-	-
18 & Above	-	*	-	-	-	*	*	*	-	-
<b>Average</b>	<b>0.24</b>	<b>0.20</b>	<b>0.50</b>	<b>0.49</b>	<b>0.40</b>	<b>0.36</b>	<b>0.22</b>	<b>0.30</b>	<b>0.43</b>	<b>0.42</b>
UNIFORMITY 2/										
74 & Below	0.1	0.1	-	-	-	-	*	*	-	-
75	0.2	0.2	-	-	-	-	0.3	0.2	-	-
76	0.5	0.6	-	*	-	*	0.9	0.6	-	-
77	1.4	1.9	0.1	0.1	*	*	3.5	2.1	*	*
78	5.6	6.3	0.5	0.4	0.1	0.1	10.9	6.3	0.3	0.2
79	19.8	16.3	3.3	3.2	1.9	1.4	24.1	15.0	1.7	1.3
80	34.3	30.7	14.7	17.0	15.5	14.7	31.6	25.8	8.3	6.3
81	26.9	30.9	42.1	41.6	38.6	39.1	20.2	29.5	28.8	24.3
82	10.2	11.7	29.7	28.5	33.8	31.8	6.9	16.3	43.2	45.0
83	1.0	1.4	8.0	7.9	9.3	11.1	1.5	3.7	15.6	19.9
84	0.1	0.1	1.4	1.2	0.7	1.5	0.2	0.4	2.0	2.8
85 & Above	*	*	0.1	0.1	*	0.1	*	*	0.1	0.2
<b>Average</b>	<b>80.57</b>	<b>80.66</b>	<b>81.72</b>	<b>81.68</b>	<b>81.80</b>	<b>81.86</b>	<b>80.23</b>	<b>80.82</b>	<b>82.15</b>	<b>82.30</b>
Tenderable 3/	<b>82.8</b>	<b>85.9</b>	<b>93.3</b>	<b>93.1</b>	<b>93.1</b>	<b>89.2</b>	<b>70.9</b>	<b>80.9</b>	<b>92.0</b>	<b>92.1</b>
<b>SAMPLES CLASSED</b>	<b>33,480</b>	<b>130,761</b>	<b>21,869</b>	<b>67,958</b>	<b>79,276</b>	<b>342,819</b>	<b>431,485</b>	<b>2,888,632</b>	<b>13,333</b>	<b>20,013</b>

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. \* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Nov 19, 2020**

Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	-	-	14.7	14.5	-	-	38.1	27.4
	2	-	-	5.3	5.5	-	-	16.7	11.9
	3	-	-	*	*	-	-	0.3	0.3
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total -----</b>		-	-	<b>20.0</b>	<b>20.0</b>	-	-	<b>55.1</b>	<b>39.7</b>
02	1	-	-	31.5	35.7	-	-	18.0	24.2
	2	-	-	40.2	37.3	-	-	25.0	32.0
	3	-	-	1.3	1.0	-	-	1.2	2.1
	4	-	-	*	*	-	-	-	*
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total -----</b>		-	-	<b>73.0</b>	<b>74.0</b>	-	-	<b>44.2</b>	<b>58.4</b>
03	1	-	-	2.3	1.7	-	-	0.1	0.3
	2	-	-	3.7	3.7	-	-	0.4	1.0
	3	-	-	0.5	0.3	-	-	0.2	0.6
	4	-	-	*	*	-	-	-	*
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total -----</b>		-	-	<b>6.5</b>	<b>5.8</b>	-	-	<b>0.6</b>	<b>1.9</b>
04	1	-	-	0.3	0.1	-	-	-	-
	2	-	-	0.2	0.1	-	-	*	*
	3	-	-	*	*	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total -----</b>		-	-	<b>0.5</b>	<b>0.2</b>	-	-	<b>*</b>	<b>*</b>
05	1	-	-	*	*	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total -----</b>		-	-	<b>*</b>	<b>*</b>	-	-	-	-
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total -----</b>		-	-	-	-	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total -----</b>		-	-	-	-	-	-	-	-
<b>STAPLE</b>									
44 & Shorter		-	-	1.4	1.9	-	-	6.5	7.2
46		-	-	1.9	12.6	-	-	14.8	25.2
48		-	-	24.2	24.1	-	-	63.6	57.7
50		-	-	68.0	57.2	-	-	12.9	8.0
52 & Longer		-	-	4.4	4.2	-	-	2.2	1.9
<b>Average Staple</b>		-	-	<b>49.44</b>	<b>48.98</b>	-	-	<b>47.79</b>	<b>47.44</b>
<b>Average Length</b>		-	-	<b>1.44</b>	<b>1.42</b>	-	-	<b>1.39</b>	<b>1.38</b>
<b>EXTRANEIOUS MATTER</b>									
Bark		-	-	*	*	-	-	0.1	0.2
Grass		-	-	*	0.3	-	-	0.1	0.6
Spindle Twist		-	-	*	*	-	-	0.2	1.0
Preparation		-	-	*	*	-	-	0.5	0.2
All Other		-	-	*	*	-	-	0.1	0.3

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Nov 19, 2020**

Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5 - 2.6	-	-	-	-	-	-	0.1	0.1
2.7 - 2.9	-	-	-	-	-	-	3.5	1.5
3.0 - 3.2	-	-	-	*	-	-	10.2	6.4
3.3 - 3.4	-	-	*	0.4	-	-	4.0	4.4
3.5 - 3.6	-	-	0.3	2.7	-	-	2.5	7.7
3.7 - 4.2	-	-	23.8	34.0	-	-	52.7	51.6
4.3 - 4.9	-	-	75.8	62.9	-	-	26.9	28.3
5.0 - 5.2	-	-	0.1	0.1	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
<b>Average</b>	-	-	<b>4.37</b>	<b>4.28</b>	-	-	<b>3.97</b>	<b>3.98</b>
ALL RANGE MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5	-	-	-	-	-	-	-	-
2.6	-	-	-	-	-	-	0.1	0.1
2.7	-	-	-	-	-	-	0.7	0.3
2.8	-	-	-	-	-	-	1.3	0.6
2.9	-	-	-	-	-	-	1.6	0.7
3.0	-	-	-	*	-	-	2.5	1.3
3.1	-	-	-	*	-	-	3.4	2.3
3.2	-	-	-	*	-	-	4.3	2.9
3.3	-	-	*	0.1	-	-	2.4	2.1
3.4	-	-	*	0.2	-	-	1.6	2.3
3.5	-	-	0.1	1.0	-	-	1.5	3.2
3.6	-	-	0.2	1.7	-	-	1.0	4.5
3.7	-	-	0.6	2.5	-	-	1.7	4.4
3.8	-	-	1.6	3.6	-	-	1.7	4.5
3.9	-	-	3.3	5.3	-	-	4.6	7.5
4.0	-	-	4.5	5.7	-	-	11.6	9.8
4.1	-	-	5.6	6.9	-	-	19.7	12.6
4.2	-	-	8.1	9.9	-	-	13.4	12.8
4.3	-	-	16.5	14.9	-	-	7.9	10.5
4.4	-	-	22.3	18.4	-	-	13.6	12.7
4.5	-	-	16.6	13.4	-	-	3.4	3.8
4.6	-	-	11.3	9.1	-	-	2.0	1.3
4.7	-	-	6.6	5.1	-	-	0.1	*
4.8	-	-	2.2	1.7	-	-	-	-
4.9	-	-	0.3	0.3	-	-	-	-
5.0	-	-	0.1	0.1	-	-	-	-
5.1	-	-	*	*	-	-	-	-
5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
<b>Average</b>	-	-	<b>4.37</b>	<b>4.28</b>	-	-	<b>3.97</b>	<b>3.98</b>
STRENGTH 1/								
36 & Below	-	-	*	0.2	-	-	8.5	6.3
37	-	-	0.1	2.9	-	-	4.5	5.8
38	-	-	1.7	7.5	-	-	3.3	6.4
39	-	-	2.1	4.4	-	-	1.6	4.8
40	-	-	2.1	1.6	-	-	4.7	10.3
41	-	-	4.1	3.2	-	-	6.2	9.9
42	-	-	7.9	7.7	-	-	13.8	11.1
43	-	-	16.9	17.6	-	-	15.9	14.6
44	-	-	26.0	23.0	-	-	15.7	14.7
45	-	-	25.2	19.8	-	-	18.4	11.0
46	-	-	10.4	9.3	-	-	6.1	4.2
47	-	-	2.7	2.1	-	-	1.0	0.6
48 & Above	-	-	0.8	0.7	-	-	0.3	0.2
<b>Average</b>	-	-	<b>44.27</b>	<b>43.55</b>	-	-	<b>42.69</b>	<b>42.03</b>
UNIFORMITY								
83 & Below	-	-	0.3	0.4	-	-	2.7	1.8
84	-	-	2.9	8.5	-	-	7.9	7.5
85	-	-	7.2	11.9	-	-	11.3	19.0
86	-	-	43.5	39.0	-	-	44.7	48.0
87	-	-	43.4	37.6	-	-	33.0	23.3
88 & Above	-	-	2.7	2.7	-	-	0.5	0.4
<b>Average</b>	-	-	<b>86.78</b>	<b>86.57</b>	-	-	<b>86.45</b>	<b>86.29</b>
<b>Samples Classed</b>	-	-	<b>42,447</b>	<b>120,913</b>	-	-	<b>3,856</b>	<b>8,889</b>

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

\* Less than 0.05 percent.