



Classing Office	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
Abilene	38	67.8	55.7	61,024	40	75.0	62.5	603,602
Corpus Christi	15	30.8	19.8	8,751	54	55.6	32.5	1,712,622
Dumas	26	69.3	39.8	38,538	40	78.0	50.2	1,333,293
Florence	34	72.5	46.5	31,234	53	77.9	59.6	1,149,938
Lamesa	33	62.7	49.7	64,400	36	73.4	60.0	611,035
Lubbock	70	68.6	51.6	283,051	72	73.3	58.8	2,514,645
Macon	73	58.8	48.7	125,425	79	74.7	61.6	2,031,643
Memphis	34	66.3	47.8	36,975	81	61.9	44.1	2,865,484
Rayville	11	46.0	25.4	13,566	21	55.8	31.4	487,592
Visalia	23	83.6	64.9	30,863	33	81.4	62.2	369,904
United States	357	66.0	49.9	693,827	509	69.4	51.4	13,679,758
AMERICAN PIMA								
Visalia	19			36,322	23			499,678
United States	19			36,322	23			499,678
United States all cotton	373			730,149	522			14,179,436

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 03 2019

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 11 & 21	1-2	Pct. 3.4	Pct. 2.2	Pct. 2.4	Pct. 17.2	Pct. *	Pct. 0.4	Pct. *	Pct. 0.1	Pct. 5.6	Pct. 5.2
	3	2.6	2.2	2.3	10.8	*	0.7	0.3	0.3	4.3	3.7
	4	0.3	0.2	0.1	0.7	*	0.1	0.1	*	0.2	0.4
	5	*	*	-	*	-	*	-	*	*	*
	6	-	*	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	*	-	-	-	-	-	-
	Total	----	6.3	4.6	4.8	28.7	0.1	1.2	0.4	0.4	10.1
31	1-2	11.8	8.6	1.7	5.8	0.6	1.7	0.7	1.9	11.6	9.9
	3	27.2	25.0	1.0	11.7	5.5	13.5	7.0	14.3	28.0	26.3
	4	8.0	7.8	0.1	3.4	2.6	6.7	5.3	7.2	11.6	10.9
	5	0.8	0.8	-	0.2	0.2	0.4	0.6	0.6	1.5	1.7
	6	*	*	-	*	*	*	*	*	0.2	0.1
	7	-	*	-	*	-	-	-	-	*	*
	8	-	*	-	*	-	-	*	*	-	-
	Total	----	47.8	42.3	2.8	21.1	9.0	22.4	13.6	24.1	52.9
41	1-2	1.6	2.4	0.2	1.7	0.7	0.9	0.7	1.8	0.4	1.2
	3	12.5	16.8	1.8	5.6	20.3	17.3	16.1	23.9	5.2	8.9
	4	11.4	13.8	0.6	2.7	38.7	33.3	27.6	23.7	6.7	11.2
	5	4.6	4.5	-	0.4	11.1	10.8	7.4	5.3	3.6	5.3
	6	0.8	0.7	-	*	0.5	0.7	0.7	0.4	1.0	1.5
	7	0.1	0.1	-	*	*	*	*	*	0.2	0.4
	8	-	*	-	*	-	*	-	*	-	-
	Total	----	31.0	38.4	2.6	10.5	71.3	63.1	52.5	55.1	17.1
51	1-2	*	0.1	2.6	0.4	*	*	*	0.1	*	*
	3	0.2	0.4	11.7	2.0	1.0	0.4	1.9	1.4	*	*
	4	0.4	0.7	8.2	1.3	4.5	1.8	7.2	2.1	0.1	0.1
	5	0.4	0.8	1.0	0.3	3.3	1.7	5.1	1.2	0.1	0.2
	6	0.2	0.4	*	*	0.4	0.3	1.0	0.2	*	0.3
	7	0.1	0.1	*	*	*	*	0.1	*	0.1	0.2
	8	*	*	-	*	-	*	-	*	-	-
	Total	----	1.3	2.4	23.6	4.1	9.3	4.2	15.3	5.0	0.3
61	1-2	-	-	*	*	-	-	-	*	-	-
	3	-	-	1.0	0.1	*	*	*	*	-	-
	4	-	-	0.8	0.1	-	*	*	*	-	-
	5	*	*	0.1	*	-	-	*	*	-	-
	6	*	*	-	*	-	*	*	*	-	*
	7	-	*	-	*	-	-	-	*	-	-
	8	-	*	-	*	-	-	-	*	-	-
	Total	----	*	*	2.0	0.3	*	*	0.1	*	-
71	1-2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-
	4	-	-	*	*	-	-	-	-	-	-
	5	-	-	-	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	-	-	*	*	-	-	-	-	-
12 & 22	1-2	0.2	0.2	1.6	4.2	-	*	*	*	0.5	0.5
	3	0.4	0.4	0.3	4.0	*	*	*	*	1.3	0.9
	4	*	0.1	-	0.7	-	*	-	*	0.3	0.2
	5	*	*	-	*	-	-	-	*	*	*
	6	-	-	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	*	-	-	-	-	-	-
	Total	----	0.7	0.7	1.9	9.0	*	*	0.1	*	2.1
32	1-2	0.6	0.4	-	1.1	*	*	0.1	0.1	0.6	0.4
	3	2.1	1.7	*	3.2	0.5	0.4	1.1	1.0	4.1	2.5
	4	1.1	1.2	-	1.6	0.5	0.4	0.8	0.5	3.3	2.1
	5	0.4	0.3	-	0.2	*	*	0.1	0.1	1.3	0.6
	6	0.1	*	-	*	-	*	*	*	0.3	0.1
	7	*	*	-	*	-	-	-	-	0.1	*
	8	-	-	-	*	-	-	-	-	-	-
	Total	----	4.2	3.6	*	6.1	1.0	0.9	2.1	1.8	9.7
42	1-2	0.3	0.2	0.1	0.5	*	*	0.1	0.4	*	0.1
	3	2.0	1.4	0.1	2.9	0.9	1.1	1.8	4.6	0.5	0.8
	4	1.9	1.6	0.1	2.4	3.5	3.2	4.4	4.0	0.9	1.0
	5	1.0	0.8	-	0.6	1.4	1.4	1.9	0.8	0.7	0.7
	6	0.4	0.2	-	0.1	0.1	0.1	0.3	0.1	0.4	0.3
	7	0.1	*	-	*	-	*	*	*	0.1	0.1
	8	*	*	-	*	-	-	-	*	-	-
	Total	----	5.6	4.3	0.3	6.5	5.9	5.8	8.6	9.9	2.6

* Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 03 2019

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 52	1-2	*	*	0.2	0.2	-	*	*	0.1	-	*
	3	0.2	0.2	5.7	1.7	0.1	0.1	0.3	0.9	0.1	*
	4	0.4	0.3	18.1	2.3	0.7	0.6	1.2	1.0	0.1	*
	5	0.2	0.3	7.7	0.9	0.4	0.7	1.2	0.4	*	*
	6	0.1	0.1	0.3	0.2	0.1	0.2	0.5	0.1	*	*
	7	*	*	-	*	*	*	0.1	*	*	*
	8	*	*	-	*	*	*	-	*	-	-
	Total	----	0.9	1.0	32.0	5.3	1.3	1.5	3.3	2.5	0.1
62	1-2	-	*	0.3	*	-	*	-	*	-	*
	3	-	0.1	1.8	0.3	-	*	*	*	-	*
	4	*	*	3.4	0.6	-	*	0.1	*	-	*
	5	-	-	1.4	0.3	-	*	*	*	-	*
	6	-	*	0.3	*	-	*	*	*	-	*
	7	-	*	*	*	*	*	0.1	*	-	-
	8	-	*	-	*	*	*	0.1	*	-	-
	Total	----	*	0.1	7.2	1.2	*	*	0.3	0.1	-
13 & 23	1-2	*	*	0.6	0.4	-	-	-	*	*	*
	3	0.1	0.1	0.2	0.5	-	-	*	*	0.1	0.1
	4	*	0.1	*	0.2	*	*	-	*	*	0.1
	5	-	*	-	*	-	-	-	-	-	*
	6	-	-	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	0.1	0.2	0.9	1.1	*	*	*	*	0.2
33	1-2	*	*	*	0.1	-	*	-	*	0.1	*
	3	0.2	0.3	-	0.4	*	*	0.2	0.1	0.9	0.3
	4	0.2	0.4	-	0.3	0.1	*	0.2	0.1	1.1	0.6
	5	0.1	0.1	-	0.1	*	*	*	*	0.4	0.3
	6	0.1	*	-	*	-	-	*	*	0.2	*
	7	*	*	-	*	-	-	-	*	*	*
	8	-	*	-	*	-	-	*	*	-	-
	Total	----	0.5	0.9	*	0.9	0.1	0.1	0.4	0.1	2.7
43	1-2	*	*	0.2	*	-	*	*	*	*	*
	3	0.2	0.1	0.2	0.4	0.1	0.1	0.4	0.2	0.2	0.1
	4	0.4	0.2	0.1	0.5	0.7	0.3	1.0	0.3	0.5	0.1
	5	0.2	0.2	*	0.2	0.3	0.1	0.5	0.1	0.5	0.2
	6	0.1	0.1	-	0.1	0.1	*	0.2	*	0.2	0.1
	7	0.1	*	-	*	*	*	*	*	*	*
	8	0.1	*	-	*	-	-	-	*	-	-
	Total	----	1.0	0.7	0.5	1.3	1.3	0.5	2.1	0.7	1.4
53	1-2	*	*	*	*	-	-	*	*	*	*
	3	0.1	*	0.4	0.4	*	*	0.1	0.1	0.2	*
	4	0.2	*	0.7	0.8	0.2	0.1	0.3	0.1	*	*
	5	*	*	0.7	0.5	0.2	0.1	0.2	0.1	*	*
	6	*	*	0.1	0.1	0.1	*	0.2	*	-	*
	7	*	*	-	*	*	*	*	*	*	*
	8	*	*	-	*	*	*	*	*	-	-
	Total	----	0.3	0.2	2.0	1.9	0.5	0.2	0.8	0.2	0.2
63	1-2	-	*	-	*	-	-	-	*	-	-
	3	-	*	0.2	0.1	-	*	-	*	-	-
	4	*	*	3.6	0.5	-	*	*	*	-	-
	5	*	*	7.4	0.5	-	*	*	*	-	-
	6	*	*	1.8	0.2	-	*	-	*	-	-
	7	-	-	*	*	-	-	*	*	-	-
	8	-	*	-	*	-	-	*	*	-	-
	Total	----	*	*	13.1	1.3	-	*	*	*	-
24 - 54	1-8	0.1	0.6	0.2	0.4	0.2	0.1	0.5	0.1	0.6	0.2
25 - 35	1-8	-	0.1	-	*	-	-	-	-	-	-
81 - 85	1-8	*	0.1	6.1	0.4	-	-	*	*	-	*
STAPLE											
28 & Shorter		-	*	-	-	-	-	-	-	-	-
29		-	*	*	*	-	-	-	*	-	-
30		*	*	0.1	0.2	-	-	*	*	-	*
31		0.2	0.1	0.7	0.8	-	-	*	*	0.1	*
32		0.5	0.8	0.9	2.3	*	*	0.2	0.1	0.4	0.4
33		3.2	3.1	1.9	5.7	0.2	0.2	3.2	1.1	2.1	2.5
34		9.2	7.7	10.5	12.3	1.2	1.9	9.4	6.2	11.8	10.3
35		16.1	14.7	26.5	18.4	4.4	6.6	19.2	17.7	21.6	23.4
36		23.1	24.2	15.3	22.3	10.8	13.7	21.1	24.2	26.0	26.2
37		26.5	28.8	31.0	21.9	28.2	28.5	31.9	28.0	26.4	24.1
38		14.8	13.5	12.1	10.5	26.3	27.4	12.5	17.3	7.5	9.4
39		5.4	6.0	0.9	4.7	23.1	17.6	2.3	4.8	2.8	3.0
40 & Longer		1.1	1.2	*	0.7	5.8	4.0	0.2	0.5	1.5	0.5
Average Staple		36.30	36.35	35.97	35.85	37.66	37.41	36.16	36.45	36.03	36.00
Average Length		1.13	1.13	1.12	1.12	1.18	1.17	1.13	1.14	1.12	1.12

1/ Below Grade Color. 2/ Below Grade Leaf. * Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 03 2019

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA		
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	
Color 11 & 21	1-2	5.9	4.1	0.1	0.9	*	0.5	*	0.6	18.0	28.3	
	3	7.1	4.9	0.1	1.7	0.2	0.5	0.6	1.2	7.4	7.3	
	4	1.0	0.7	*	0.2	*	*	0.1	0.1	0.2	0.2	
	5	*	*	-	*	-	*	-	*	0.1	*	
	6	-	*	-	-	-	-	-	-	-	-	
	7	-	-	-	-	-	-	-	-	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	Total	----	14.0	9.7	0.2	2.7	0.2	1.1	0.7	1.9	25.7	35.9
	31	1-2	11.4	9.5	0.6	3.0	0.4	0.9	0.2	2.6	15.6	12.2
3		29.8	26.3	5.0	20.7	5.0	5.6	8.2	14.9	21.4	14.7	
4		12.6	11.8	2.6	10.0	2.9	3.1	6.0	5.9	4.3	2.5	
5		1.8	1.9	0.2	0.6	0.3	0.3	0.8	0.4	0.9	0.3	
6		0.1	0.1	*	*	*	*	-	*	0.1	*	
7		*	*	-	*	-	-	-	-	*	*	
8		-	*	-	-	-	-	-	-	-	-	
Total		----	55.7	49.7	8.4	34.4	8.5	9.8	15.2	23.9	42.4	29.8
41		1-2	0.8	1.2	2.3	1.3	0.4	1.6	1.2	1.9	3.8	4.0
	3	6.0	9.9	21.2	16.9	12.6	18.1	22.1	18.1	10.6	12.6	
	4	6.9	12.1	23.7	21.4	28.1	25.9	21.1	18.2	7.0	6.1	
	5	3.5	5.7	5.8	4.8	10.2	7.8	2.6	3.9	1.9	1.2	
	6	1.0	1.4	0.5	0.3	1.0	0.6	0.1	0.2	0.3	0.2	
	7	0.2	0.2	*	*	*	*	-	*	0.1	*	
	8	*	*	*	*	-	*	-	-	*	*	
	Total	----	18.4	30.7	53.5	44.6	52.3	54.0	47.1	42.2	23.6	24.0
	51	1-2	-	*	0.2	*	*	0.1	0.8	0.5	*	0.1
3		*	*	3.3	0.9	1.8	1.5	4.2	2.3	0.2	1.0	
4		*	0.1	6.4	2.0	7.2	4.6	1.9	1.9	0.4	1.1	
5		0.1	0.2	3.2	1.2	8.5	3.4	0.1	0.5	0.3	0.4	
6		0.1	0.2	0.6	0.2	1.9	0.5	-	0.1	0.1	0.1	
7		*	0.1	0.1	*	0.1	*	-	*	*	*	
8		*	*	*	*	-	*	-	*	-	*	
Total		----	0.2	0.6	13.6	4.4	19.4	10.1	7.0	5.3	1.0	2.7
61		1-2	-	-	-	-	-	-	*	*	-	-
	3	-	-	*	*	*	*	0.3	*	-	*	
	4	-	-	*	*	0.1	*	0.3	*	-	-	
	5	-	-	*	*	0.1	*	*	*	-	-	
	6	-	-	*	*	*	*	*	*	-	-	
	7	-	*	-	*	*	*	-	-	-	-	
	8	-	*	-	*	-	-	-	*	-	*	
	Total	----	-	*	*	*	0.3	*	0.7	0.1	-	*
	71	1-2	-	-	-	-	-	-	-	-	-	-
3		-	-	-	*	-	-	-	-	-	-	
4		-	-	-	*	-	-	-	-	-	-	
5		-	-	-	-	-	-	-	-	-	-	
6		-	-	-	-	-	-	-	-	-	-	
7		-	-	-	-	-	-	-	-	-	-	
8		-	-	-	*	-	-	-	-	-	-	
Total		----	-	-	-	*	-	-	-	-	-	-
12 & 22		1-2	0.4	0.3	*	*	-	*	-	0.1	0.3	1.1
	3	0.7	0.5	*	0.1	*	*	-	0.2	0.9	0.7	
	4	0.2	0.2	*	*	*	*	*	*	0.1	0.2	
	5	*	*	-	*	-	*	-	*	*	*	
	6	-	*	-	-	-	-	-	-	-	-	
	7	-	*	-	-	-	-	-	-	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	Total	----	1.3	1.0	*	0.1	*	0.1	*	0.4	1.4	2.0
	32	1-2	1.0	0.5	0.1	0.3	*	0.2	*	0.2	0.2	0.3
3		3.7	2.1	1.0	1.8	0.7	0.9	0.5	1.3	1.3	1.2	
4		1.8	1.7	0.7	1.0	0.9	0.5	1.9	0.8	0.4	0.3	
5		0.5	0.5	0.1	0.1	0.1	0.1	1.8	0.2	0.1	0.1	
6		0.1	*	*	*	*	*	0.2	*	*	*	
7		*	*	-	-	-	*	-	*	*	*	
8		-	*	-	-	-	-	-	-	*	*	
Total		----	7.1	4.8	1.9	3.2	1.7	1.6	4.4	2.5	2.1	2.0
42		1-2	0.1	0.1	0.2	0.1	*	0.5	0.3	0.4	*	0.1
	3	0.5	0.7	3.7	2.3	1.3	6.7	4.9	5.2	0.5	0.9	
	4	0.6	1.0	6.3	3.4	5.5	8.8	5.5	5.9	1.7	1.1	
	5	0.4	0.5	2.2	1.0	4.2	2.5	1.1	1.5	0.7	0.3	
	6	0.1	0.1	0.2	0.1	0.8	0.2	0.1	0.1	*	0.1	
	7	*	*	*	*	0.1	*	*	*	*	*	
	8	*	*	-	*	-	-	-	-	*	*	
	Total	----	1.7	2.5	12.6	6.9	12.0	18.8	11.8	13.0	3.0	2.4

* Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 03 2019

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 52	1-2	-	*	*	*	-	*	0.2	0.2	*	*
	3	*	*	0.5	0.2	0.1	0.4	3.2	1.9	0.1	0.1
	4	*	*	1.8	0.7	1.1	1.3	2.7	2.8	0.1	0.3
	5	*	*	1.4	0.5	1.7	0.9	0.4	1.1	0.1	0.2
	6	*	*	0.3	0.1	0.4	0.2	*	0.2	*	*
	7	*	*	*	*	*	*	-	*	*	*
	8	*	*	*	*	-	*	-	-	-	*
	Total	----	*	0.1	4.2	1.6	3.3	2.7	6.6	6.2	0.3
62	1-2	-	*	-	-	-	-	0.1	*	-	*
	3	-	*	*	*	-	*	0.3	0.2	-	*
	4	-	*	*	*	-	*	0.4	0.2	-	*
	5	-	*	*	*	*	*	0.1	0.1	*	*
	6	-	*	*	*	*	*	*	*	-	-
	7	-	-	*	*	*	*	-	*	-	-
	8	-	-	*	*	*	*	-	-	-	*
	Total	----	-	*	0.1	*	*	*	0.9	0.6	*
13 & 23	1-2	0.1	*	*	*	-	*	-	*	-	*
	3	0.1	*	*	*	-	*	*	*	-	0.1
	4	*	*	-	*	-	*	-	*	*	*
	5	*	*	-	-	-	-	-	-	-	*
	6	*	*	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	0.2	0.1	*	*	-	*	*	*	*
33	1-2	0.1	*	*	*	*	*	-	*	-	*
	3	0.4	0.2	0.1	0.2	0.1	*	0.1	0.1	0.1	*
	4	0.4	0.2	0.2	0.1	0.1	*	0.1	*	0.1	*
	5	0.1	0.1	*	*	*	*	0.1	*	0.1	*
	6	*	*	*	*	-	*	0.1	*	*	*
	7	-	*	-	-	-	*	-	-	*	*
	8	-	*	-	-	-	-	-	-	*	*
	Total	----	1.0	0.5	0.4	0.4	0.2	0.1	0.3	0.1	0.4
43	1-2	*	*	*	*	*	*	*	*	-	*
	3	*	*	0.9	0.3	0.1	0.4	0.9	0.5	*	*
	4	0.1	0.1	1.8	0.5	0.7	0.6	0.9	0.8	*	0.1
	5	0.1	0.1	0.8	0.2	0.5	0.2	0.3	0.3	*	0.1
	6	*	*	0.1	*	0.2	*	0.2	*	*	*
	7	*	*	*	*	*	*	*	*	*	*
	8	*	*	-	-	-	*	-	*	*	*
	Total	----	0.2	0.2	3.7	1.1	1.5	1.3	2.4	1.6	0.1
53	1-2	*	*	*	*	-	*	*	*	-	-
	3	*	*	0.1	*	*	*	1.1	0.4	-	*
	4	*	*	0.3	0.1	0.1	0.1	0.9	0.7	*	*
	5	*	*	0.3	0.1	0.3	0.1	0.2	0.5	-	*
	6	*	*	0.1	*	0.1	*	*	0.1	-	*
	7	*	*	*	*	*	*	-	*	-	*
	8	-	*	*	*	-	*	-	-	-	*
	Total	----	*	*	0.9	0.3	0.5	0.3	2.2	1.6	*
63	1-2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	*	-	*	*	0.1	-	-
	4	-	*	*	*	-	*	0.1	0.1	-	-
	5	-	*	*	*	-	*	0.1	0.1	-	-
	6	-	-	*	*	-	*	*	*	-	-
	7	-	-	*	*	-	-	-	*	-	-
	8	-	-	*	*	-	*	-	-	-	-
	Total	----	-	*	0.1	*	-	*	0.3	0.4	-
24 - 54	1-8	0.1	0.1	0.4	0.2	0.1	0.1	0.3	0.2	*	*
25 - 35	1-8	-	-	*	*	-	*	-	*	-	-
81 - 85	1-8	-	*	0.1	*	*	*	0.1	*	*	*
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	*	-	-	-	-	-	-	-	-
30		*	*	-	*	-	*	*	*	-	-
31		*	*	*	*	-	*	*	0.1	-	*
32		0.4	0.3	0.1	0.1	*	*	0.4	0.4	-	*
33		2.6	1.8	1.5	1.0	*	0.1	2.3	1.5	*	0.2
34		10.4	8.0	7.9	5.3	0.5	0.9	4.8	4.3	0.7	1.4
35		23.8	20.5	14.7	13.3	3.0	6.3	19.2	12.1	4.6	5.7
36		27.7	27.5	18.9	18.5	13.4	19.8	20.0	18.1	11.8	14.0
37		24.6	27.3	28.5	30.3	48.0	39.4	25.4	26.2	25.6	27.7
38		7.4	9.8	19.0	22.7	20.8	21.3	16.8	19.9	29.2	21.3
39		2.5	3.8	8.1	8.0	9.6	9.1	7.8	12.6	17.9	16.7
40 & Longer		0.6	1.0	1.4	0.9	4.7	3.2	3.3	4.8	10.3	13.0
Average Staple		35.96	36.20	36.61	36.76	37.34	37.14	36.58	36.96	37.75	37.67
Average Length		1.12	1.13	1.14	1.15	1.17	1.16	1.14	1.15	1.18	1.18

1/ Below Grade Color. 2/ Below Grade Leaf. * Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 03 2019

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	18.6	11.8	2.5	1.4	3.5	1.2	4.8	2.4	15.0	10.0
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	*	-	0.7	0.1	0.2	0.1	0.1	*	*
Grass - Level 2	-	-	-	-	-	*	-	-	-	-
Prep - Level 1	-	*	-	*	2.3	0.6	0.1	*	-	*
Prep - Level 2	-	-	-	-	*	*	-	-	-	-
Seed Coat - Level 1	*	*	24.2	3.5	0.6	0.1	0.1	*	*	*
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	*	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	*	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	*	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	0.1	0.1	*	*	*	*	*	*
Plastic - Level 2	-	-	-	-	*	*	-	-	-	-
STRENGTH 1/22 & Below	*	*	0.3	0.4	-	-	0.1	*	*	*
23	*	0.1	0.8	0.7	-	-	0.5	0.1	*	*
24	0.1	0.2	3.0	1.5	*	*	2.0	0.3	0.1	0.1
25	0.4	0.5	9.1	2.9	0.3	0.2	6.6	1.7	0.3	0.4
26	1.6	1.7	20.6	5.2	1.2	1.0	16.1	4.8	2.0	2.1
27	6.8	5.7	27.0	9.0	5.2	4.0	24.6	9.8	5.5	6.3
28	15.1	14.5	23.3	15.6	17.6	12.7	25.3	18.1	12.6	15.3
29	22.5	22.2	10.0	21.1	27.8	28.4	14.2	24.0	21.4	21.0
30	22.2	22.1	3.4	19.8	26.5	29.7	6.2	19.6	22.4	21.8
31	15.3	16.0	1.6	13.0	13.6	15.4	2.8	11.7	17.2	18.1
32	9.8	10.2	0.7	6.2	5.4	5.8	1.0	6.0	11.2	9.6
33	4.2	4.7	0.1	2.7	1.7	2.1	0.4	2.8	4.3	3.7
34	1.2	1.5	0.1	1.2	0.5	0.6	0.1	0.9	1.9	1.1
35	0.5	0.4	-	0.4	0.1	0.1	*	0.2	0.9	0.4
36	0.1	0.1	-	0.1	*	*	*	*	0.2	0.1
37	*	*	-	*	-	-	-	*	*	*
38	*	*	-	*	-	-	-	*	-	-
39	-	*	-	-	-	-	-	-	-	-
40 & Above	-	-	-	-	-	-	-	-	-	-
Average	30.18	30.24	27.57	29.54	29.91	30.11	27.99	29.62	30.38	30.18
Mike										
2.4 & Below	*	*	-	*	-	-	-	*	0.2	0.1
2.5	0.3	0.1	-	*	*	*	-	-	1.1	0.4
2.6	0.2	0.1	-	*	*	*	-	*	1.5	0.5
2.7	0.2	0.1	-	*	*	*	-	*	1.4	0.6
2.8	0.2	0.2	-	*	*	*	-	*	1.7	0.7
2.9	0.2	0.2	-	*	*	*	*	*	2.0	0.8
3.0	0.3	0.3	-	0.1	*	*	-	*	2.1	1.0
3.1	0.6	0.5	-	0.1	*	*	-	*	2.4	1.2
3.2	1.0	0.7	-	0.2	*	*	*	*	2.8	1.5
3.3	1.2	1.0	-	0.2	*	*	*	*	2.9	2.0
3.4	1.8	1.4	-	0.3	-	*	0.1	0.1	3.6	2.3
3.5	2.0	1.7	*	0.4	*	*	0.1	0.2	4.2	3.0
3.6	2.0	2.1	0.1	0.4	*	*	0.4	0.3	4.9	3.9
3.7	2.4	3.0	0.3	0.7	*	0.1	0.7	0.5	5.8	4.7
3.8	3.2	3.7	0.1	1.0	*	0.3	1.4	0.9	6.0	5.4
3.9	4.9	4.7	0.3	1.4	0.2	0.5	2.7	1.6	7.1	6.3
4.0	6.5	6.0	0.6	1.9	0.4	0.9	4.8	2.8	7.8	7.4
4.1	7.6	7.5	1.2	2.7	1.4	1.7	6.0	4.4	6.8	8.1
4.2	8.9	8.4	2.0	3.9	3.6	2.7	8.5	6.4	7.2	8.5
4.3	9.1	9.1	3.9	5.5	5.6	4.2	10.6	8.4	6.8	8.9
4.4	10.0	9.8	6.7	7.3	5.6	6.3	13.6	10.8	5.8	7.8
4.5	9.7	10.1	11.0	9.1	7.3	9.3	13.6	13.1	5.2	7.3
4.6	7.9	9.1	19.0	10.6	9.6	13.6	12.1	14.4	4.1	6.0
4.7	6.8	7.4	15.2	11.2	13.5	16.9	8.7	13.2	2.5	4.3
4.8	5.0	5.3	16.3	10.7	17.2	16.9	6.5	9.9	1.5	3.1
4.9	3.5	3.5	10.5	9.1	15.0	13.2	4.6	6.1	1.0	2.2
5.0	2.7	2.0	7.0	7.2	10.2	7.4	2.9	3.6	0.6	1.1
5.1	1.1	1.2	3.4	5.6	5.5	3.5	1.4	1.9	0.4	0.6
5.2	0.5	0.6	1.9	4.1	2.8	1.5	0.8	0.9	0.4	0.3
5.3	0.1	0.2	0.3	2.9	1.3	0.7	0.3	0.3	0.1	0.1
5.4	*	0.1	*	2.0	0.4	0.2	0.1	0.1	*	*
5.5 & Above	*	*	*	1.3	0.2	*	0.1	*	*	*
Average	4.27	4.29	4.68	4.67	4.73	4.69	4.45	4.53	3.89	4.09

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 03 2019

Quality Designation	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	8.6	8.5	22.3	13.7	6.0	1.0	14.1	3.8	0.9	0.7
Bark - Level 2	-	-	-	*	-	-	-	-	-	-
Grass - Level 1	*	*	*	0.1	0.3	0.1	*	0.1	*	*
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	*	*	0.1	0.1	*	*	-	*	-	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	0.9	0.2	*	0.1	0.1	0.1	0.1	0.9
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	*	*	-	-	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	*	-	*	*	*
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	*	*	*	*	-	*	-	*	-	-
Other - Level 2	-	*	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	-	-	*	*	-	*	*	*	-	-
23	*	*	*	*	-	*	0.1	0.1	-	-
24	0.1	*	0.4	0.3	*	*	0.2	0.3	*	*
25	0.3	0.2	1.7	1.8	0.2	0.2	0.7	0.9	*	*
26	1.3	0.8	6.6	6.9	2.5	1.8	3.3	2.5	0.2	0.1
27	4.7	3.0	14.1	15.9	11.3	7.9	7.7	5.7	1.7	1.1
28	11.9	8.4	21.2	25.7	25.3	21.4	24.0	11.6	4.3	4.5
29	18.1	15.3	23.2	25.1	29.4	29.5	29.7	24.6	8.7	10.4
30	21.3	20.7	16.7	14.8	18.6	21.0	17.5	26.1	15.9	15.8
31	20.2	22.0	9.0	6.3	8.6	10.9	8.8	15.8	16.9	16.3
32	13.6	16.7	4.3	2.2	2.9	5.1	5.0	8.1	15.7	15.2
33	5.9	8.6	1.7	0.7	0.7	1.8	2.1	3.1	11.6	11.6
34	1.8	3.1	0.7	0.2	0.3	0.4	0.5	1.0	8.7	7.0
35	0.5	0.9	0.2	0.1	*	0.1	0.1	0.3	7.7	5.2
36	0.1	0.2	*	*	*	*	*	0.1	3.6	5.9
37	0.1	0.1	*	*	-	*	*	*	2.9	4.8
38	0.1	*	*	*	-	-	-	*	1.9	1.7
39	*	*	-	*	-	*	-	-	0.2	0.2
40 & Above	-	*	-	*	-	-	-	-	0.1	0.1
Average	30.58	31.00	29.27	28.96	29.39	29.69	29.54	30.11	32.37	32.43
Mike										
2.4 & Below	0.2	0.1	-	-	-	-	-	-	-	*
2.5	0.5	0.2	-	*	-	*	-	*	*	*
2.6	0.7	0.3	*	*	-	*	-	*	0.1	*
2.7	0.8	0.3	*	*	-	*	-	*	*	0.1
2.8	1.1	0.4	*	*	-	*	*	*	0.1	0.1
2.9	1.5	0.6	*	*	-	*	-	*	0.1	0.1
3.0	1.8	0.9	0.1	*	-	*	*	*	0.5	0.2
3.1	2.2	1.2	0.1	0.1	*	*	*	*	0.2	0.2
3.2	2.8	1.6	0.2	0.2	*	*	-	*	0.3	0.3
3.3	3.1	2.1	0.3	0.4	0.1	*	-	*	0.5	0.5
3.4	3.6	2.7	0.6	0.7	0.1	0.1	-	*	0.9	0.8
3.5	4.3	3.4	1.0	1.1	0.2	0.1	*	*	1.1	0.9
3.6	5.0	4.1	1.4	1.6	0.6	0.2	*	0.1	1.1	1.2
3.7	5.1	4.7	2.0	2.4	0.9	0.4	0.2	0.1	1.8	1.6
3.8	5.5	5.5	3.0	3.6	1.6	0.7	0.3	0.2	2.7	2.1
3.9	5.8	6.3	4.3	5.5	2.0	1.1	1.0	0.5	4.3	2.9
4.0	6.2	6.8	5.8	8.0	2.9	1.7	0.8	0.7	5.1	3.6
4.1	6.4	7.2	8.7	10.6	4.4	2.8	2.0	1.4	5.6	4.9
4.2	6.3	7.3	11.9	13.0	5.6	4.4	2.5	2.4	6.8	6.3
4.3	6.6	7.3	13.8	13.5	9.7	6.2	4.1	3.3	8.2	7.5
4.4	6.1	7.0	14.4	12.2	11.1	8.5	4.9	4.4	7.4	8.8
4.5	5.6	6.6	12.1	9.9	13.3	10.6	8.2	7.0	7.2	9.3
4.6	4.8	6.0	8.8	7.0	12.5	11.7	10.2	9.8	10.2	10.5
4.7	4.2	5.1	5.8	4.7	10.1	11.7	11.1	13.4	11.9	10.5
4.8	3.3	4.0	3.1	2.8	7.5	11.0	15.7	15.8	8.8	8.9
4.9	2.6	3.1	1.5	1.6	7.0	9.4	13.6	15.1	6.1	6.6
5.0	1.7	2.2	0.7	0.7	4.3	7.4	11.9	12.0	4.6	5.0
5.1	1.1	1.4	0.3	0.3	2.8	5.3	5.9	7.3	2.1	3.6
5.2	0.6	0.8	0.1	0.1	1.5	3.5	3.1	4.0	0.8	2.0
5.3	0.4	0.4	*	*	1.2	2.0	3.0	1.7	0.3	0.8
5.4	0.2	0.2	*	*	0.5	0.9	1.0	0.4	0.1	0.3
5.5 & Above	0.1	0.1	*	*	0.2	0.3	0.3	0.2	0.9	0.3
Average	4.01	4.14	4.30	4.26	4.53	4.65	4.74	4.76	4.43	4.48

1/ Fiber strength expressed in terms of 1/8" gage (grams per tax).
 * Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 03 2019

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
2.4 & Below	*	*	-	*	-	-	-	*	0.2	0.1
2.5 - 2.6	0.5	0.2	-	*	*	*	-	*	2.6	0.9
2.7 - 2.9	0.6	0.4	-	0.1	0.1	*	*	*	5.0	2.1
3.0 - 3.2	1.9	1.4	-	0.3	0.1	*	*	*	7.3	3.7
3.3 - 3.4	3.1	2.4	-	0.5	*	*	0.1	0.1	6.5	4.3
3.5 - 3.6	4.0	3.8	0.1	0.8	*	0.1	0.5	0.5	9.1	6.9
3.7 - 4.2	33.5	33.3	4.6	11.6	5.7	6.3	24.1	16.6	40.6	40.4
4.3 - 4.9	52.0	54.3	82.7	63.6	73.8	80.2	69.7	76.0	27.0	39.4
5.0 - 5.2	4.2	3.7	12.3	16.9	18.6	12.4	5.1	6.3	1.4	2.0
5.3 & Above	0.1	0.4	0.4	6.2	1.9	1.0	0.4	0.5	0.1	0.1
Average	4.27	4.29	4.68	4.67	4.73	4.69	4.45	4.53	3.89	4.09
Leaf										
1 - 2	17.9	14.2	10.1	31.7	1.5	3.1	1.7	4.7	18.9	17.4
3	47.7	48.8	27.0	44.3	28.5	33.7	29.4	46.8	44.8	43.7
4	24.4	26.8	36.8	18.5	51.6	46.4	48.3	39.1	24.7	26.7
5	7.7	8.1	21.7	4.4	17.1	15.4	17.2	8.6	8.4	9.0
6	1.9	1.7	4.4	0.9	1.3	1.4	2.9	0.8	2.5	2.5
7	0.3	0.3	0.1	0.2	0.1	*	0.3	*	0.7	0.8
8	0.1	0.1	-	*	*	*	0.1	*	-	-
Average	3.28	3.35	3.82	2.96	3.89	3.78	3.92	3.54	3.32	3.37
HVI Trash 1/										
00	-	-	-	*	-	-	-	-	*	*
01	3.2	2.0	3.1	7.9	*	0.2	0.1	0.3	3.9	3.7
02	18.9	15.5	8.2	26.1	2.8	4.9	2.6	6.3	20.4	17.7
03	25.1	24.9	13.4	25.0	12.5	15.7	11.7	20.7	25.1	23.7
04	20.1	21.4	17.8	17.5	21.3	22.8	21.8	26.3	19.0	19.5
05	12.9	14.5	17.2	10.5	23.2	22.0	23.2	20.8	12.3	13.3
06	8.1	9.0	13.5	5.9	18.8	16.2	17.4	12.9	7.5	8.5
07	4.7	5.4	9.4	3.2	11.8	9.7	10.8	6.8	4.8	5.3
08	2.9	3.1	7.0	1.7	5.5	4.9	5.8	3.3	2.9	3.2
09	1.7	1.8	4.5	0.9	2.5	2.2	3.2	1.5	1.7	2.0
10	0.9	1.0	3.0	0.5	1.0	0.9	1.7	0.6	1.1	1.2
11	0.6	0.6	1.7	0.3	0.4	0.3	0.8	0.2	0.7	0.8
12	0.3	0.3	0.7	0.2	0.1	0.1	0.5	0.1	0.4	0.5
13	0.2	0.2	0.3	0.1	0.1	*	0.2	*	0.2	0.3
14	0.1	0.1	0.1	0.1	*	*	0.1	*	0.1	0.2
15	*	0.1	*	*	*	*	0.1	*	*	0.1
16	*	*	-	*	*	*	*	*	*	*
17	*	*	-	*	*	*	*	*	*	*
18 & Above	0.1	*	-	*	*	*	*	*	*	*
Average	0.41	0.43	0.52	0.35	0.52	0.50	0.54	0.46	0.40	0.42
UNIFORMITY 2/										
74 & Below	*	*	*	0.1	-	-	*	*	*	*
75	0.1	*	0.7	0.4	-	-	0.1	*	0.1	*
76	0.3	0.3	2.6	1.3	-	-	0.4	0.1	0.6	0.4
77	1.8	1.7	7.6	3.1	0.3	0.2	1.8	0.8	2.8	1.6
78	8.3	6.8	27.1	6.2	2.3	1.5	10.3	4.3	10.3	5.8
79	25.1	21.2	36.8	12.2	11.2	8.2	30.4	18.0	24.5	19.5
80	35.4	34.7	18.4	21.5	30.2	29.7	36.1	35.9	33.2	34.7
81	22.2	25.3	5.5	26.3	34.8	39.3	16.1	29.1	19.8	26.7
82	6.0	8.4	1.2	20.7	17.0	17.4	4.1	10.0	7.6	9.5
83	0.8	1.4	0.1	7.3	3.8	3.3	0.6	1.6	1.1	1.8
84	*	0.2	-	0.9	0.4	0.4	0.1	0.2	*	0.1
85 & Above	*	0.1	-	*	*	*	*	*	-	*
Average	80.34	80.51	79.27	80.97	81.10	81.19	80.13	80.70	80.27	80.59
Tenderables	67.8	75.0	30.8	55.6	69.3	78.0	72.5	77.9	62.7	73.4
SAMPLES CLASSIFIED										
Week	61,024		8,751		38,538		31,234		64,400	
Season		603,602		1,712,622		1,333,293		1,149,938		611,035

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on New York No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 03 2019

Quality MIKE	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
2.4 & Below	0.2	0.1	-	-	-	-	-	-	-	*
2.5 - 2.6	1.2	0.5	*	*	-	*	-	*	0.1	0.1
2.7 - 2.9	3.4	1.4	0.1	*	-	*	*	*	0.3	0.2
3.0 - 3.2	6.7	3.7	0.3	0.3	*	*	*	*	1.0	0.7
3.3 - 3.4	6.6	4.8	1.0	1.1	0.1	0.1	-	*	1.4	1.3
3.5 - 3.6	9.4	7.5	2.4	2.7	0.8	0.4	*	0.1	2.2	2.1
3.7 - 4.2	35.2	37.9	35.7	43.1	17.4	11.1	6.9	5.3	26.4	21.4
4.3 - 4.9	33.2	39.0	59.5	51.6	71.2	69.1	67.9	68.9	59.7	62.2
5.0 - 5.2	3.4	4.4	1.0	1.2	8.5	16.2	20.8	23.3	7.5	10.6
5.3 & Above	0.6	0.7	*	*	1.9	3.1	4.3	2.3	1.4	1.5
Average	4.01	4.14	4.30	4.26	4.53	4.65	4.74	4.76	4.43	4.48
Leaf										
1 - 2	19.6	15.7	3.6	5.8	0.8	3.9	2.9	6.6	38.0	46.2
3	48.5	44.9	35.9	45.3	21.8	34.2	46.5	46.3	42.4	38.7
4	23.7	28.1	44.1	39.6	46.8	44.9	41.9	37.5	14.5	12.0
5	6.4	9.0	14.3	8.5	25.8	15.3	7.8	8.7	4.2	2.5
6	1.4	1.9	1.9	0.8	4.5	1.6	0.9	0.8	0.6	0.4
7	0.3	0.4	0.2	0.1	0.3	*	*	0.1	0.2	0.1
8	*	0.1	*	*	*	*	-	*	*	*
Average	3.22	3.37	3.75	3.53	4.12	3.77	3.57	3.51	2.84	2.65
HVI Trash 1/										
00	-	*	-	-	-	-	-	-	-	*
01	3.0	2.3	0.4	0.5	*	0.3	0.1	0.6	10.1	16.7
02	21.1	16.7	4.7	7.6	1.2	4.6	5.1	9.4	32.5	34.0
03	27.4	23.8	15.2	20.9	8.1	14.2	21.7	22.7	25.8	23.9
04	20.5	20.5	22.0	25.3	17.4	21.5	28.4	24.8	14.4	12.6
05	12.6	14.6	21.3	20.4	20.8	21.6	20.4	18.9	8.3	6.5
06	6.9	9.3	15.7	12.7	19.6	16.6	11.6	11.6	4.7	3.2
07	3.7	5.6	9.8	6.8	14.1	10.5	5.8	6.3	2.0	1.5
08	2.0	3.2	5.5	3.2	8.9	5.7	3.3	3.1	1.0	0.7
09	1.2	1.8	2.8	1.4	4.9	2.8	1.7	1.4	0.4	0.4
10	0.7	1.0	1.4	0.6	2.5	1.3	0.8	0.6	0.3	0.2
11	0.4	0.6	0.7	0.3	1.3	0.5	0.5	0.3	0.2	0.1
12	0.2	0.3	0.3	0.1	0.6	0.2	0.4	0.1	0.1	0.1
13	0.1	0.2	0.1	0.1	0.2	0.1	0.1	0.1	*	*
14	0.1	0.1	0.1	*	0.1	*	0.1	*	0.1	*
15	*	0.1	*	*	*	*	*	*	*	*
16	*	*	*	*	*	*	-	-	*	*
17	*	*	*	*	*	*	-	-	*	*
18 & Above	*	*	*	*	*	*	-	-	*	*
Average	0.38	0.42	0.51	0.46	0.59	0.51	0.46	0.45	0.31	0.28
UNIFORMITY 2/										
74 & Below	-	-	-	-	-	-	*	0.1	-	*
75	0.1	*	-	*	-	-	*	0.1	-	*
76	0.2	0.1	*	*	*	*	0.3	0.3	*	*
77	1.1	0.6	0.2	0.2	*	0.1	1.0	1.3	0.2	0.1
78	5.4	3.2	1.5	1.8	0.5	0.5	4.7	5.3	1.0	0.8
79	16.8	12.1	8.3	10.1	3.3	3.4	18.4	15.6	4.6	4.2
80	32.0	28.8	29.3	33.5	18.1	15.6	30.1	29.9	16.8	14.6
81	29.4	33.6	39.4	37.1	42.3	33.2	33.2	31.4	33.7	31.7
82	12.2	17.2	16.8	14.2	28.9	32.9	11.0	12.6	31.8	28.3
83	2.3	3.8	3.9	2.8	6.5	13.0	1.3	3.0	9.8	11.0
84	0.3	0.4	0.5	0.3	0.4	1.2	0.1	0.5	1.5	7.7
85 & Above	*	*	*	*	*	*	-	0.1	0.5	1.5
Average	80.75	81.05	81.20	81.06	81.62	81.83	80.72	80.81	81.73	81.98
Tenderables	68.6	73.3	58.8	74.7	66.3	61.9	46.0	55.8	83.6	81.4
SAMPLES CLASSIFIED										
Week	283,051		125,425		36,975		13,566		30,863	
Season		2,514,645		2,031,643		2,865,484		487,592		369,904

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on New York No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 03 2019

Color Grade	Leaf	VISALIA		Quality Designation	VISALIA	
		Week	Season		Week	Season
01	1	17.3	19.3	MIKE		Visalia Seasonal
	2	21.8	22.2	2.4 & Below	-	*
	3	0.2	0.4	2.5 - 2.6	*	*
	4	-	*	2.7 - 2.9	0.5	0.2
	5	-	-	3.0 - 3.2	1.4	0.6
	6	-	-	3.3 - 3.4	1.9	1.2
	7	-	-	3.5 - 3.6	7.5	4.0
Total -----		39.3	41.9	3.7 - 4.2	56.3	53.9
02	1	7.1	6.0	4.3 - 4.9	32.3	40.2
	2	42.0	38.4	5.0 - 5.2	*	*
	3	5.0	7.6	5.3 & Above	*	*
	4	0.1	0.1	Average	4.07	4.14
	5	-	*	ALL RANGE MIKE		
	6	-	-	2.4 & Below	-	*
	7	-	-	2.5	*	*
Total -----		54.2	52.2	2.6	*	*
03	1	0.1	0.1	2.7	0.1	*
	2	3.3	2.6	2.8	0.1	0.1
	3	2.4	2.3	2.9	0.2	0.1
	4	0.4	0.3	3.0	0.3	0.1
	5	-	*	3.1	0.5	0.2
	6	-	*	3.2	0.6	0.3
	7	-	-	3.3	0.9	0.4
Total -----		6.2	5.4	3.4	1.0	0.7
04	1	*	*	3.5	2.8	1.5
	2	0.1	0.2	3.6	4.7	2.5
	3	0.1	0.2	3.7	6.2	3.8
	4	*	*	3.8	7.6	5.8
	5	*	*	3.9	8.4	8.4
	6	-	*	4.0	11.7	10.6
	7	-	*	4.1	11.2	11.7
Total -----		0.3	0.5	4.2	11.2	13.7
05	1	-	-	4.3	9.6	14.7
	2	-	*	4.4	9.8	12.7
	3	*	*	4.5	7.9	7.9
	4	-	*	4.6	4.0	3.5
	5	-	-	4.7	0.8	1.1
	6	-	-	4.8	0.2	0.2
	7	-	-	4.9	*	*
Total -----		*	0.1	5.0	*	*
06	1	-	-	5.1	-	*
	2	-	-	5.2	-	*
	3	-	*	5.3 & Above	*	*
	4	*	*	Average	4.07	4.14
	5	-	-	STRENGTH 1/		
	6	-	-	36 & Below	0.2	0.3
	7	-	-	37	0.3	0.6
Total -----		*	*	38	2.5	1.9
07	1	-	-	39	4.6	3.6
	2	-	-	40	5.6	3.8
	3	-	*	41	3.9	4.4
	4	-	*	42	9.2	9.7
	5	-	-	43	14.8	17.6
	6	-	-	44	17.1	23.9
	7	-	-	45	19.5	20.2
Total -----		-	*	46	13.8	9.3
STAPLE	44 & Shorter	0.2	0.2	47	5.6	3.3
	46	5.7	5.0	48 & Above	3.0	1.5
	48	32.4	35.6	Average	44.13	43.99
	50	55.6	53.2	UNIFORMITY		
	52 & Longer	6.1	6.0	83 & Below	1.7	0.9
Average Staple		49.23	49.20	84	8.8	5.3
Average Length		1.43	1.43	85	29.7	21.6
EXTRANEEOUS MATTER	Bark	*	*	86	45.5	53.8
	Grass	*	0.2	87	13.2	17.0
	Spindle Twist	0.4	0.1	88 & Above	1.0	1.3
	Preparation	*	*	Average	86.07	86.30
	All Other	*	*	Samples Classed		
				Week	36,322	
				Season		499,678

* Less than 0.05 percent.