



Volume 62, No.12

Classing Office	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
<b>UPLAND</b>								
Abilene	20	84.4	70.6	26,921	21	80.3	63.6	35,646
Corpus Christi	40	79.0	62.0	133,050	49	86.2	74.1	1,235,980
Dumas	37	90.6	68.1	102,387	38	91.0	70.6	246,584
Florence	8	92.3	77.3	2,594	10	93.4	81.6	4,989
Lamesa	19	93.1	74.1	21,195	20	93.1	72.3	39,769
Lubbock	60	83.8	66.5	111,441	60	83.2	63.3	166,414
Macon	51	67.6	57.8	83,064	51	66.1	56.0	116,758
Memphis	67	91.7	77.4	201,166	67	90.1	74.8	332,968
Rayville	19	83.3	67.8	55,684	19	87.2	71.0	147,230
Visalia	10	94.6	72.8	14,457	10	92.3	56.7	34,460
<b>United States</b>	<b>331</b>	<b>84.7</b>	<b>68.5</b>	<b>751,959</b>	<b>345</b>	<b>86.3</b>	<b>71.6</b>	<b>2,360,798</b>
<b>AMERICAN PIMA</b>								
Visalia	3			2,256	3			4,943
United States	3			2,256	3			4,943
<b>United States all cotton</b>	<b>333</b>			<b>754,215</b>	<b>347</b>			<b>2,365,741</b>

\* Data withheld to avoid disclosure of individual gin or less than 500 bales classed.

**QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE**  
**For The Week Ending Oct 22, 2020**

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 11 & 21	1-2	Pct. 75.6	Pct. 69.6	Pct. 12.5	Pct. 13.6	Pct. 0.8	Pct. 1.2	Pct. 0.3	Pct. 0.4	Pct. 81.6	Pct. 80.0
	3	5.1	6.0	11.8	11.7	1.5	2.4	0.2	0.7	6.7	4.7
	4	0.5	0.5	1.3	0.9	0.1	0.1	-	0.1	0.2	0.1
	5	-	-	0.1	*	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>81.3</b>	<b>76.1</b>	<b>25.5</b>	<b>26.3</b>	<b>2.4</b>	<b>3.7</b>	<b>0.6</b>	<b>1.2</b>	<b>88.5</b>
31	1-2	3.2	4.7	4.7	5.3	3.5	2.9	2.9	3.3	0.1	0.1
	3	3.1	4.7	20.8	25.3	30.1	29.9	38.4	33.7	0.5	0.3
	4	1.1	1.6	10.1	9.9	17.5	18.0	14.1	15.0	0.1	0.1
	5	0.3	0.3	1.1	0.9	1.1	1.4	0.3	1.0	-	-
	6	*	*	0.1	*	*	*	-	*	-	-
	7	*	*	*	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>7.8</b>	<b>11.3</b>	<b>36.7</b>	<b>41.4</b>	<b>52.1</b>	<b>52.2</b>	<b>55.7</b>	<b>53.0</b>	<b>0.8</b>
41	1-2	*	*	1.8	1.1	0.4	0.3	0.2	0.1	-	*
	3	*	*	7.5	8.2	11.2	9.6	7.1	8.2	*	*
	4	0.1	0.1	4.9	6.7	24.1	23.6	25.7	26.2	-	-
	5	0.1	0.1	1.2	1.4	7.7	8.7	7.1	7.5	-	-
	6	*	*	0.3	0.2	0.5	0.7	0.3	0.5	-	-
	7	*	*	*	*	*	*	-	-	-	-
	8	-	-	*	*	-	-	-	-	-	-
	<b>Total</b>	----	<b>0.2</b>	<b>0.3</b>	<b>15.8</b>	<b>17.5</b>	<b>43.9</b>	<b>42.9</b>	<b>40.4</b>	<b>42.6</b>	<b>*</b>
51	1-2	-	-	0.1	*	-	*	-	-	-	-
	3	-	-	0.5	0.4	0.1	*	-	-	-	-
	4	-	-	0.2	0.3	0.2	0.1	0.1	0.3	-	-
	5	-	-	0.1	0.1	0.1	0.1	-	0.4	-	-
	6	-	-	*	*	0.1	*	-	0.1	-	-
	7	-	-	-	*	*	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	-	-	<b>0.9</b>	<b>0.8</b>	<b>0.5</b>	<b>0.3</b>	<b>0.1</b>	<b>0.7</b>	-
61	1-2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	-	-	-	<b>*</b>	-	-	-	-	-
71	1-2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	-	-	-	<b>*</b>	-	-	-	-	-
12 & 22	1-2	4.5	4.3	1.4	1.4	-	-	-	-	8.2	12.0
	3	1.7	2.4	1.8	1.3	*	*	0.1	0.1	1.6	1.6
	4	0.5	0.6	0.2	0.2	-	-	*	*	*	*
	5	0.1	0.1	*	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>6.8</b>	<b>7.3</b>	<b>3.4</b>	<b>2.9</b>	<b>*</b>	<b>*</b>	<b>0.2</b>	<b>0.2</b>	<b>9.9</b>
32	1-2	0.2	0.2	0.5	0.3	*	*	-	-	0.1	0.1
	3	0.3	0.4	3.1	1.7	0.1	0.1	0.6	0.6	0.2	0.1
	4	0.4	0.5	2.1	1.1	0.2	0.1	0.2	0.3	*	*
	5	0.3	0.3	0.3	0.3	*	*	*	*	-	-
	6	0.1	0.1	*	*	-	-	-	-	-	-
	7	*	*	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>1.3</b>	<b>1.5</b>	<b>6.1</b>	<b>3.5</b>	<b>0.3</b>	<b>0.3</b>	<b>0.8</b>	<b>0.9</b>	<b>0.3</b>
42	1-2	-	-	0.4	0.2	*	*	-	-	*	*
	3	-	*	2.1	1.3	0.1	0.1	0.7	0.4	-	-
	4	*	0.1	2.1	1.6	0.3	0.3	1.3	0.8	-	-
	5	0.2	0.2	0.7	0.7	0.2	0.1	0.2	0.1	-	-
	6	*	0.1	0.2	0.2	*	*	-	-	-	-
	7	*	*	0.1	*	-	-	-	-	-	-
	8	-	*	*	*	-	-	-	-	-	-
	<b>Total</b>	----	<b>0.2</b>	<b>0.4</b>	<b>5.7</b>	<b>4.0</b>	<b>0.7</b>	<b>0.5</b>	<b>2.2</b>	<b>1.4</b>	<b>*</b>

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE**  
**For The Week Ending Oct 22, 2020**

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 52	1-2	-	-	0.2	0.1	-	*	-	-	-	-
	3	-	-	1.0	0.5	*	*	-	-	-	-
	4	-	-	0.8	0.6	*	*	-	0.1	-	-
	5	-	-	0.5	0.4	*	*	-	*	-	-
	6	-	-	0.2	0.1	*	*	-	-	-	-
	7	-	-	*	*	-	-	-	-	-	-
	8	-	-	*	*	-	-	-	-	-	-
	<b>Total</b>	----	-	-	<b>2.7</b>	<b>1.6</b>	<b>*</b>	<b>*</b>	-	<b>0.1</b>	-
62	1-2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	*	*	*	-	-	-	-
	5	-	-	-	*	*	-	-	-	-	-
	6	-	-	-	*	*	-	-	-	-	-
	7	-	-	-	*	*	-	-	-	-	-
	8	-	-	-	*	*	-	-	-	-	-
	<b>Total</b>	----	-	-	-	<b>*</b>	<b>*</b>	-	-	-	-
13 & 23	1-2	0.7	0.7	0.1	0.1	-	-	*	*	0.2	0.4
	3	0.6	0.7	0.1	0.1	-	-	-	-	0.1	0.2
	4	0.1	0.1	*	*	-	-	-	-	-	*
	5	*	*	*	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>1.3</b>	<b>1.4</b>	<b>0.1</b>	<b>0.2</b>	-	-	<b>*</b>	<b>*</b>	<b>0.4</b>
33	1-2	0.1	0.1	*	*	-	-	-	-	*	*
	3	0.2	0.4	0.1	0.1	*	*	-	-	0.1	0.1
	4	0.1	0.2	0.1	0.1	*	*	-	-	*	*
	5	*	0.1	*	*	*	*	-	-	*	*
	6	*	0.1	*	*	-	-	-	-	-	-
	7	*	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>0.5</b>	<b>0.9</b>	<b>0.2</b>	<b>0.2</b>	<b>*</b>	<b>*</b>	-	-	<b>0.1</b>
43	1-2	-	-	*	*	-	-	-	-	-	-
	3	*	*	0.3	0.1	*	*	-	-	-	-
	4	-	-	0.5	0.3	*	*	-	-	-	-
	5	*	*	0.2	0.2	*	*	-	-	-	-
	6	0.1	0.1	*	*	-	-	-	-	-	-
	7	*	0.1	*	*	-	-	-	-	-	-
	8	-	*	*	*	-	-	-	-	-	-
	<b>Total</b>	----	<b>0.1</b>	<b>0.2</b>	<b>1.1</b>	<b>0.7</b>	<b>*</b>	<b>*</b>	-	-	-
53	1-2	*	*	*	*	-	-	-	-	-	-
	3	-	*	0.4	0.1	-	*	-	-	-	-
	4	-	-	0.5	0.2	-	*	-	-	-	-
	5	*	*	0.4	0.2	-	*	-	-	-	-
	6	*	*	0.3	0.2	-	-	-	-	-	-
	7	*	*	*	0.1	-	-	-	-	-	-
	8	*	*	*	*	-	-	-	-	-	-
	<b>Total</b>	----	<b>*</b>	<b>*</b>	<b>1.7</b>	<b>0.8</b>	-	<b>*</b>	-	-	-
63	1-2	-	-	-	*	-	-	-	-	-	-
	3	-	-	*	*	-	*	-	-	-	-
	4	-	-	*	*	-	*	-	-	-	-
	5	-	-	*	*	-	*	-	-	-	-
	6	-	-	*	*	-	-	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	*	-	-	-	-	-	-
	<b>Total</b>	----	-	<b>*</b>	<b>*</b>	<b>*</b>	-	<b>*</b>	-	-	-
24 - 54	1-8	0.2	0.4	*	0.1	*	*	-	-	*	0.1
25 - 35	1-8	0.1	*	-	-	-	-	-	-	-	-
81 - 85	1-8	0.2	0.1	*	*	*	*	-	-	-	-
STAPLE											
28 & Shorter		-	*	-	-	-	-	-	-	-	-
29		-	*	*	*	-	-	-	-	-	*
30		0.1	0.1	0.1	*	-	-	-	-	*	0.2
31		1.1	1.3	0.5	0.1	-	-	-	-	0.4	0.4
32		4.4	4.8	1.0	0.4	-	-	-	-	2.0	2.4
33		7.4	8.7	2.0	1.1	*	*	-	-	6.8	8.4
34		9.9	11.5	4.3	3.6	0.1	0.1	0.1	*	18.6	20.1
35		8.2	9.0	12.3	11.6	0.8	1.0	7.1	4.9	24.5	23.9
36		11.6	13.4	24.5	26.5	4.8	4.7	17.2	10.6	20.7	21.1
37		25.3	24.7	31.8	34.9	18.4	20.0	22.4	19.1	17.1	16.8
38		19.7	17.0	15.6	15.3	26.7	28.2	34.8	39.9	7.9	5.5
39		9.2	7.0	5.7	5.2	32.9	31.2	17.1	20.9	1.4	0.8
40 & Longer		3.1	2.4	2.3	1.2	16.3	14.7	1.2	4.5	0.7	0.4
<b>Average Staple</b>		<b>36.31</b>	<b>36.04</b>	<b>36.55</b>	<b>36.62</b>	<b>38.37</b>	<b>38.29</b>	<b>37.41</b>	<b>37.75</b>	<b>35.47</b>	<b>35.29</b>
<b>Average Length</b>		<b>1.13</b>	<b>1.13</b>	<b>1.14</b>	<b>1.14</b>	<b>1.20</b>	<b>1.20</b>	<b>1.17</b>	<b>1.18</b>	<b>1.11</b>	<b>1.10</b>

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE**  
**For The Week Ending Oct 22, 2020**

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA		
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	
Color 11 & 21	1-2	Pct. 82.9	Pct. 80.4	Pct. 0.2	Pct. 0.2	Pct. 3.7	Pct. 4.3	Pct. 3.5	Pct. 5.1	Pct. 76.9	Pct. 67.5	
	3	5.7	5.1	0.4	0.4	1.1	1.3	4.1	7.3	5.5	4.0	
	4	0.2	0.2	*	*	*	*	0.2	0.5	0.3	0.2	
	5	*	*	-	-	-	-	*	*	-	-	
	6	-	-	-	-	-	-	-	-	-	-	
	7	-	-	-	-	-	-	-	-	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	<b>Total</b>	----	<b>88.8</b>	<b>85.8</b>	<b>0.7</b>	<b>0.7</b>	<b>4.8</b>	<b>5.7</b>	<b>7.8</b>	<b>12.9</b>	<b>82.7</b>	<b>71.7</b>
	31	1-2	0.1	0.2	2.0	1.8	11.0	11.4	2.0	2.8	9.0	4.1
3		0.2	0.2	15.5	14.1	31.7	31.3	18.1	25.2	3.3	2.0	
4		0.1	0.2	7.8	7.3	11.4	11.2	13.5	14.2	0.9	0.6	
5		*	0.1	0.5	0.4	0.6	0.6	0.9	0.7	*	*	
6		-	*	*	*	*	*	*	*	-	-	
7		-	-	-	-	-	-	-	-	-	-	
8		-	-	-	-	-	-	-	-	-	-	
<b>Total</b>		----	<b>0.5</b>	<b>0.7</b>	<b>25.8</b>	<b>23.6</b>	<b>54.8</b>	<b>54.6</b>	<b>34.6</b>	<b>42.9</b>	<b>13.2</b>	<b>6.7</b>
41		1-2	*	*	0.4	0.3	0.4	0.4	0.4	0.4	*	*
	3	*	*	13.7	12.8	10.2	9.8	13.2	10.9	-	-	
	4	-	*	24.4	24.6	19.9	19.3	25.5	19.9	*	*	
	5	-	*	6.9	7.0	6.2	6.5	5.8	4.1	-	-	
	6	-	*	0.5	0.5	0.4	0.4	0.2	0.2	-	-	
	7	-	*	*	*	-	*	-	-	-	-	
	8	-	-	*	*	-	-	-	-	-	-	
	<b>Total</b>	----	<b>*</b>	<b>*</b>	<b>46.0</b>	<b>45.3</b>	<b>37.1</b>	<b>36.5</b>	<b>45.2</b>	<b>35.4</b>	<b>*</b>	<b>*</b>
	51	1-2	-	-	-	-	*	*	-	-	-	-
3		*	*	0.3	0.3	*	*	*	*	-	-	
4		-	-	1.3	1.4	0.1	0.1	0.3	0.5	-	-	
5		-	-	1.3	1.5	0.2	0.1	0.2	0.3	-	-	
6		-	-	0.2	0.3	0.1	*	*	*	-	-	
7		-	-	*	*	-	-	-	-	-	-	
8		-	-	-	-	-	-	-	-	-	-	
<b>Total</b>		----	<b>*</b>	<b>*</b>	<b>3.1</b>	<b>3.5</b>	<b>0.3</b>	<b>0.2</b>	<b>0.6</b>	<b>0.8</b>	-	-
61		1-2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	
	4	-	-	-	-	-	-	-	-	-	-	
	5	-	-	-	-	-	-	-	-	-	-	
	6	-	-	-	-	-	-	-	-	-	-	
	7	-	-	-	-	-	-	-	-	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	<b>Total</b>	----	-	-	-	-	-	-	-	-	-	-
	71	1-2	-	-	-	-	-	-	-	-	-	-
3		-	-	-	-	-	-	-	-	-	-	
4		-	-	-	-	-	-	-	-	-	-	
5		-	-	-	-	-	-	-	-	-	-	
6		-	-	-	-	-	-	-	-	-	-	
7		-	-	-	-	-	-	-	-	-	-	
8		-	-	-	-	-	-	-	-	-	-	
<b>Total</b>		----	-	-	-	-	-	-	-	-	-	-
12 & 22		1-2	7.8	10.0	*	*	*	*	0.1	0.1	3.1	17.7
	3	1.7	2.0	*	0.1	*	*	0.2	0.2	0.8	3.3	
	4	0.1	0.1	*	*	*	*	*	*	*	0.1	
	5	*	*	-	-	-	-	-	-	-	-	
	6	-	-	-	-	-	-	-	-	-	-	
	7	-	-	-	-	-	-	-	-	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	<b>Total</b>	----	<b>9.5</b>	<b>12.0</b>	<b>*</b>	<b>0.1</b>	<b>0.1</b>	<b>0.1</b>	<b>0.3</b>	<b>0.2</b>	<b>4.0</b>	<b>21.1</b>
	32	1-2	*	*	0.1	0.2	0.3	0.2	0.2	0.2	*	0.1
3		*	*	1.0	1.6	1.0	0.9	1.9	1.6	0.1	*	
4		*	*	0.5	0.7	0.2	0.4	1.6	1.0	*	*	
5		*	*	*	*	*	0.1	0.4	0.2	-	-	
6		-	*	-	-	-	*	0.1	*	-	-	
7		-	-	-	-	-	-	-	-	-	-	
8		-	-	-	-	-	-	-	-	-	-	
<b>Total</b>		----	<b>0.1</b>	<b>0.1</b>	<b>1.7</b>	<b>2.5</b>	<b>1.6</b>	<b>1.6</b>	<b>4.2</b>	<b>2.9</b>	<b>0.1</b>	<b>0.2</b>
42		1-2	-	*	0.3	0.2	*	*	*	*	-	*
	3	*	*	5.1	5.4	0.3	0.3	1.1	1.1	*	*	
	4	-	*	7.2	8.2	0.6	0.6	3.4	2.2	*	*	
	5	-	*	2.0	2.4	0.3	0.3	1.5	0.8	-	-	
	6	-	-	0.2	0.2	*	*	0.6	0.2	-	-	
	7	-	-	*	*	-	-	-	-	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	<b>Total</b>	----	<b>*</b>	<b>*</b>	<b>14.9</b>	<b>16.5</b>	<b>1.3</b>	<b>1.3</b>	<b>6.6</b>	<b>4.3</b>	<b>*</b>	<b>*</b>

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE**  
**For The Week Ending Oct 22, 2020**

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA		
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	
Color 52	1 - 2	-	*	0.1	*	-	*	*	*	-	-	
	3	*	*	0.8	0.6	*	*	*	*	-	-	
	4	-	-	1.8	1.8	*	*	0.1	0.1	-	-	
	5	-	-	1.2	1.3	*	*	*	*	-	-	
	6	-	-	0.3	0.3	*	*	*	*	-	-	
	7	-	-	*	*	-	-	-	-	-	-	
	8	-	-	*	*	-	-	-	-	-	-	
	<b>Total</b>	----	<b>*</b>	<b>*</b>	<b>4.2</b>	<b>4.1</b>	<b>*</b>	<b>0.1</b>	<b>0.2</b>	<b>0.1</b>	-	-
	62	1 - 2	-	-	-	-	-	-	-	-	-	-
3		-	-	*	*	-	-	-	-	-	-	
4		-	-	0.1	0.2	-	-	-	-	-	-	
5		-	-	0.1	0.1	-	-	*	*	-	-	
6		-	-	*	*	-	-	-	*	-	-	
7		-	-	*	*	-	-	-	-	-	-	
8		-	-	-	-	-	-	-	-	-	-	
<b>Total</b>		----	-	-	<b>0.2</b>	<b>0.3</b>	-	-	<b>*</b>	<b>*</b>	-	-
13 & 23		1 - 2	0.5	0.7	-	-	-	-	-	-	*	0.3
	3	0.4	0.4	*	*	-	-	-	-	-	*	
	4	*	*	-	*	-	-	-	-	-	*	
	5	*	*	-	-	-	-	-	-	-	-	
	6	-	-	-	-	-	-	-	-	-	-	
	7	-	-	-	-	-	-	-	-	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	<b>Total</b>	----	<b>0.9</b>	<b>1.1</b>	<b>*</b>	<b>*</b>	-	-	-	-	<b>*</b>	<b>0.3</b>
	33	1 - 2	*	*	-	*	*	*	*	*	-	*
3		0.1	0.1	*	0.1	*	*	0.1	*	-	*	
4		*	*	*	0.1	*	*	0.1	*	-	*	
5		-	*	-	-	*	*	*	*	-	-	
6		-	*	-	-	-	-	-	-	-	-	
7		-	-	-	-	-	-	-	-	-	-	
8		-	-	-	-	-	-	-	-	-	-	
<b>Total</b>		----	<b>0.1</b>	<b>0.1</b>	<b>*</b>	<b>0.2</b>	<b>*</b>	<b>*</b>	<b>0.2</b>	<b>0.1</b>	-	<b>*</b>
43		1 - 2	-	-	*	*	*	*	-	*	-	-
	3	-	*	0.3	0.4	*	*	0.1	0.1	-	-	
	4	-	-	0.7	0.7	*	*	0.2	0.1	-	-	
	5	-	-	0.2	0.2	-	-	0.1	*	-	-	
	6	-	*	*	*	-	-	*	*	-	-	
	7	-	-	-	-	-	-	-	-	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	<b>Total</b>	----	-	<b>*</b>	<b>1.2</b>	<b>1.4</b>	<b>*</b>	<b>*</b>	<b>0.4</b>	<b>0.3</b>	-	-
	53	1 - 2	-	-	*	*	-	*	-	-	-	-
3		*	*	0.3	0.3	*	*	-	*	-	-	
4		-	-	0.7	0.7	*	*	*	*	-	-	
5		-	-	0.5	0.5	-	-	*	*	-	-	
6		-	-	0.1	0.1	-	-	*	*	-	-	
7		-	-	*	*	-	-	-	-	-	-	
8		-	-	*	*	-	-	-	-	-	-	
<b>Total</b>		----	<b>*</b>	<b>*</b>	<b>1.7</b>	<b>1.5</b>	<b>*</b>	<b>*</b>	<b>*</b>	<b>*</b>	-	-
63		1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	*	*	-	-	-	-	-	-	
	4	-	-	0.2	0.1	-	-	-	-	-	-	
	5	-	-	0.1	0.1	-	*	-	-	-	-	
	6	-	-	*	*	-	-	-	-	-	-	
	7	-	-	*	*	-	-	-	-	-	-	
	8	-	-	*	*	-	-	-	-	-	-	
	<b>Total</b>	----	-	-	<b>0.3</b>	<b>0.3</b>	-	<b>*</b>	-	-	-	-
	24 - 54	1 - 8	0.1	0.1	*	*	-	*	-	-	-	-
25 - 35	1 - 8	*	*	-	-	-	-	-	-	-	-	
81 - 85	1 - 8	*	*	*	*	-	-	-	-	-	-	
STAPLE												
28 & Shorter		-	-	-	-	-	-	-	-	-	-	
29		*	*	-	-	-	-	-	-	-	-	
30		0.2	0.2	-	-	-	-	-	-	-	-	
31		0.6	0.8	*	*	-	-	-	-	-	-	
32		2.1	3.0	*	0.1	-	-	*	*	-	-	
33		6.1	8.3	0.6	0.8	*	*	0.1	*	0.1	0.1	
34		14.4	15.9	4.5	4.4	0.1	0.1	0.7	0.4	2.3	1.4	
35		20.5	20.2	10.2	10.7	1.3	1.6	2.0	3.0	7.2	5.9	
36		22.3	21.9	18.3	18.9	8.1	8.4	5.8	10.2	20.5	24.4	
37		22.2	20.5	34.1	33.8	29.3	29.6	16.5	20.0	30.7	32.1	
38		7.5	6.1	23.3	22.2	26.5	25.9	26.7	23.7	23.5	22.1	
39		3.1	2.3	7.9	8.0	22.5	22.9	30.2	25.6	14.5	13.2	
40 & Longer		1.0	0.7	1.0	1.1	12.2	11.4	17.9	17.0	1.1	0.8	
<b>Average Staple</b>		<b>35.70</b>	<b>35.49</b>	<b>36.87</b>	<b>36.85</b>	<b>37.99</b>	<b>37.96</b>	<b>38.32</b>	<b>38.11</b>	<b>37.14</b>	<b>37.10</b>	
<b>Average Length</b>		<b>1.11</b>	<b>1.11</b>	<b>1.15</b>	<b>1.15</b>	<b>1.19</b>	<b>1.19</b>	<b>1.20</b>	<b>1.19</b>	<b>1.16</b>	<b>1.16</b>	

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE**  
**For The Week Ending Oct 22, 2020**

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	3.6	3.8	2.2	1.4	1.2	0.9	0.6	0.9	0.4	0.4
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	-	0.1	0.1	0.1	0.1	0.2	0.3	*	*
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	*	*	*	0.1	0.1	-	-
Prep - Level 2	-	-	-	*	-	-	-	-	-	-
Seed Coat - Level 1	*	*	*	*	*	0.1	-	*	0.1	0.1
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	*	*	*	*	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	*	*	-	-	-	-	-	-
Other - Level 2	-	-	*	*	-	-	-	-	-	-
Plastic - Level 1	*	*	*	0.1	*	*	-	-	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
<b>STRENGTH 1/22 &amp; Below</b>	*	*	0.2	*	-	-	-	-	*	*
23	*	0.2	0.5	0.1	-	-	-	-	*	0.2
24	0.2	0.6	0.9	0.2	*	*	-	-	0.1	0.5
25	1.5	2.0	1.2	0.5	*	*	-	-	0.2	0.9
26	3.4	4.6	2.1	1.2	0.2	0.2	*	*	1.5	2.4
27	7.7	9.4	4.8	3.2	0.8	0.9	0.3	0.3	6.3	8.0
28	11.6	11.7	9.8	7.9	4.1	4.2	1.5	3.1	15.4	18.3
29	15.5	15.1	16.6	17.1	18.2	16.6	6.9	12.2	16.2	17.9
30	18.2	16.2	19.1	22.5	36.7	33.1	29.5	28.4	18.0	16.7
31	18.9	17.1	16.2	19.5	24.3	25.2	32.5	29.8	14.5	14.4
32	13.1	13.0	12.2	13.1	9.9	11.5	16.0	15.1	12.7	10.2
33	6.0	6.8	9.6	8.8	4.2	5.7	8.2	7.1	11.2	7.5
34	2.6	2.3	4.5	4.0	1.3	1.9	4.4	3.4	3.3	2.6
35	0.8	0.7	1.8	1.5	0.2	0.5	0.5	0.6	0.4	0.5
36	0.2	0.2	0.3	0.4	*	*	0.1	0.1	0.1	0.1
37	0.1	0.1	0.1	0.1	*	*	-	-	*	*
38	*	*	*	*	-	-	-	-	-	-
39	*	*	-	*	-	-	-	-	-	-
40 & Above	-	-	-	-	-	-	-	-	-	-
<b>Average</b>	<b>30.40</b>	<b>30.22</b>	<b>30.68</b>	<b>30.91</b>	<b>30.79</b>	<b>30.92</b>	<b>31.45</b>	<b>31.24</b>	<b>30.61</b>	<b>30.19</b>
Mike										
2.4 & Below	*	*	-	-	-	-	-	-	-	-
2.5	0.1	*	-	*	-	-	-	-	-	-
2.6	0.3	0.2	*	*	-	-	-	-	-	-
2.7	0.1	0.1	*	*	-	-	-	-	*	*
2.8	*	*	*	*	-	-	-	-	-	-
2.9	0.4	0.3	0.1	0.1	-	-	-	-	*	*
3.0	0.6	0.5	0.1	0.1	*	*	-	-	0.1	*
3.1	0.5	0.5	0.3	0.2	*	*	-	-	0.2	0.2
3.2	0.3	1.1	0.3	0.2	*	*	-	-	0.3	0.2
3.3	0.8	1.7	0.6	0.4	*	*	-	-	0.4	0.3
3.4	1.6	2.8	1.0	0.7	*	*	-	-	0.4	0.4
3.5	3.7	4.9	1.1	1.0	0.2	0.1	-	*	1.0	1.0
3.6	4.4	5.7	1.3	1.6	0.3	0.2	-	0.1	1.3	1.6
3.7	3.5	4.2	2.0	2.4	0.2	0.3	-	0.1	1.8	2.4
3.8	4.3	4.6	2.5	3.8	0.4	0.6	0.2	0.6	2.4	2.7
3.9	5.6	5.3	4.1	5.4	0.8	1.1	0.6	2.3	4.2	4.4
4.0	8.8	8.1	6.1	7.3	1.5	1.7	4.5	5.2	6.0	6.6
4.1	11.1	10.5	7.1	9.0	2.5	3.2	11.6	10.6	6.6	8.1
4.2	13.2	12.2	9.0	10.4	4.6	5.0	8.1	9.6	8.6	11.2
4.3	12.8	11.6	9.0	11.0	6.4	7.6	5.9	7.0	11.7	11.5
4.4	9.9	8.7	8.9	10.9	9.5	10.4	11.6	12.7	11.1	10.6
4.5	7.7	7.0	9.4	10.2	12.4	12.6	11.9	12.0	11.9	11.7
4.6	4.9	4.6	10.2	8.7	15.5	14.5	12.6	13.3	14.9	13.2
4.7	2.7	2.6	8.9	6.6	16.3	15.3	13.3	11.1	8.2	6.8
4.8	1.6	1.5	7.3	4.5	12.6	12.0	9.2	7.3	4.1	3.5
4.9	0.7	0.6	5.5	2.8	9.9	8.6	6.1	4.8	2.8	2.2
5.0	0.3	0.5	2.4	1.5	4.0	4.1	2.5	2.0	1.2	0.8
5.1	0.1	0.1	1.4	0.8	2.0	1.7	1.2	0.8	0.3	0.4
5.2	*	*	1.1	0.3	0.7	0.7	0.6	0.3	0.1	0.1
5.3	*	*	0.3	0.1	0.2	0.2	0.2	0.1	0.2	0.1
5.4	-	-	*	*	*	*	-	-	0.2	0.1
5.5 & Above	-	-	*	*	*	*	-	-	-	-
<b>Average</b>	<b>4.12</b>	<b>4.08</b>	<b>4.38</b>	<b>4.30</b>	<b>4.60</b>	<b>4.57</b>	<b>4.49</b>	<b>4.45</b>	<b>4.35</b>	<b>4.32</b>

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE**  
**For The Week Ending Oct 22, 2020**

Quality Designation	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	2.9	2.9	1.0	1.0	0.1	0.1	3.1	1.5	*	*
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	0.2	0.2	*	*	*	*	*	0.1	*	*
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	*	*	*	*	*	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	9.1	8.4	*	*	-	-	*	*
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	*	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	*	*	*	*	-	-	*	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
<b>STRENGTH 1/</b>										
22 & Below	0.1	0.1	-	-	-	-	-	-	-	-
23	0.2	0.2	*	*	-	-	-	-	*	*
24	0.5	0.6	0.4	0.4	-	*	-	-	*	*
25	1.1	1.5	0.4	0.5	*	*	*	*	0.4	0.2
26	2.8	3.8	1.3	1.8	0.1	*	0.1	0.1	1.1	0.5
27	5.8	7.4	4.6	5.8	0.4	0.3	1.2	0.6	4.4	5.2
28	10.3	12.0	12.6	14.3	2.5	1.8	2.9	2.3	15.5	21.7
29	15.8	16.4	25.7	26.4	10.4	8.4	11.3	8.5	25.1	25.2
30	18.6	18.4	28.8	26.7	24.7	22.0	29.2	22.3	19.8	17.6
31	17.6	16.5	15.5	13.9	30.5	31.0	27.4	27.4	11.8	14.2
32	13.1	11.6	6.9	6.4	18.1	21.2	12.9	17.1	5.3	7.1
33	8.0	6.6	2.6	2.5	7.8	9.2	6.5	10.0	0.6	0.7
34	3.9	3.1	0.8	1.0	4.5	4.8	5.4	7.4	2.2	1.1
35	1.6	1.3	0.2	0.3	1.1	1.2	2.2	3.4	7.5	3.5
36	0.6	0.5	0.1	0.1	0.1	0.1	0.8	0.9	5.9	2.8
37	0.2	0.1	*	*	-	-	*	0.1	0.1	0.1
38	*	*	-	-	-	-	*	*	*	0.1
39	-	-	-	-	-	-	-	-	*	*
40 & Above	-	-	-	-	-	-	-	-	0.1	*
<b>Average</b>	<b>30.66</b>	<b>30.36</b>	<b>30.13</b>	<b>30.01</b>	<b>31.42</b>	<b>31.59</b>	<b>31.34</b>	<b>31.74</b>	<b>30.77</b>	<b>30.29</b>
Mike										
2.4 & Below	-	*	-	-	-	-	-	-	-	-
2.5	*	*	-	-	-	-	-	-	-	-
2.6	0.1	0.1	-	-	-	-	-	-	-	-
2.7	0.2	0.2	-	-	-	-	-	-	-	-
2.8	0.5	0.5	*	*	-	-	-	-	-	-
2.9	0.7	0.6	*	*	-	-	-	-	-	-
3.0	0.7	0.7	*	*	-	-	-	-	-	-
3.1	1.1	1.0	*	*	-	-	-	-	-	-
3.2	1.4	1.2	*	*	*	*	*	*	-	-
3.3	1.7	1.4	*	*	*	*	0.3	0.1	-	-
3.4	1.8	1.6	*	*	0.1	0.1	0.8	0.4	-	0.1
3.5	2.3	2.1	0.1	*	0.4	0.3	0.9	0.6	0.1	0.3
3.6	3.1	2.7	0.1	0.1	0.6	0.5	0.7	0.6	0.3	0.2
3.7	3.9	3.5	0.2	0.2	1.2	1.0	0.6	0.9	0.3	0.2
3.8	4.6	4.3	0.5	0.5	1.7	1.6	1.0	1.2	0.2	0.2
3.9	5.6	5.2	1.1	1.1	2.8	2.5	1.7	1.7	0.9	0.7
4.0	6.8	6.3	1.9	2.0	3.8	3.6	2.6	2.5	3.4	1.8
4.1	7.9	7.7	4.0	3.8	5.4	5.2	2.8	3.6	3.8	3.2
4.2	9.4	9.2	6.9	6.5	8.5	7.9	3.7	4.9	6.6	6.0
4.3	10.0	10.4	9.8	9.6	9.9	9.4	8.2	7.9	10.4	8.1
4.4	10.3	10.5	13.8	14.4	12.3	11.6	12.4	11.7	14.0	12.3
4.5	9.7	9.8	15.3	15.6	12.7	12.2	13.9	13.2	13.2	14.3
4.6	7.3	7.9	14.4	14.9	11.8	11.7	17.5	15.3	11.5	13.4
4.7	4.9	5.6	12.1	11.8	9.3	9.8	12.1	14.1	12.8	13.5
4.8	2.6	3.2	8.2	7.8	8.1	8.6	8.0	8.9	10.0	10.7
4.9	1.7	2.1	5.5	5.3	4.9	5.9	7.0	6.6	7.2	8.1
5.0	0.9	1.1	3.3	3.4	3.2	3.7	4.3	3.8	3.2	3.9
5.1	0.5	0.6	1.6	1.7	1.9	2.5	1.4	1.8	1.0	2.0
5.2	0.3	0.4	0.7	0.7	1.0	1.3	0.1	0.3	0.6	0.9
5.3	0.1	0.2	0.2	0.2	0.2	0.3	*	*	0.3	0.1
5.4	*	*	0.1	0.1	0.1	0.1	-	*	0.1	*
5.5 & Above	-	-	*	*	*	*	-	*	0.1	*
<b>Average</b>	<b>4.16</b>	<b>4.20</b>	<b>4.53</b>	<b>4.53</b>	<b>4.46</b>	<b>4.49</b>	<b>4.51</b>	<b>4.52</b>	<b>4.53</b>	<b>4.56</b>

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).  
 \* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE**  
**For The Week Ending Oct 22, 2020**

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
2.4 & Below	*	*	-	-	-	-	-	-	-	-
2.5 - 2.6	0.3	0.3	*	*	-	-	-	-	-	-
2.7 - 2.9	0.6	0.4	0.2	0.1	-	-	-	-	*	*
3.0 - 3.2	1.5	2.2	0.7	0.5	*	*	-	-	0.6	0.4
3.3 - 3.4	2.4	4.5	1.6	1.1	*	0.1	-	-	0.9	0.7
3.5 - 3.6	8.1	10.5	2.3	2.6	0.4	0.4	-	0.1	2.3	2.6
3.7 - 4.2	46.5	44.9	30.9	38.2	10.0	11.8	25.0	28.5	29.6	35.4
4.3 - 4.9	40.3	36.6	59.2	54.7	82.6	81.0	70.5	68.3	64.6	59.6
5.0 - 5.2	0.3	0.6	4.8	2.6	6.7	6.5	4.3	3.1	1.7	1.3
5.3 & Above	*	*	0.3	0.1	0.2	0.2	0.2	0.1	0.3	0.2
<b>Average</b>	<b>4.12</b>	<b>4.08</b>	<b>4.38</b>	<b>4.30</b>	<b>4.60</b>	<b>4.57</b>	<b>4.49</b>	<b>4.45</b>	<b>4.35</b>	<b>4.32</b>
Leaf										
1 - 2	84.4	79.5	21.7	22.2	4.7	4.4	3.5	3.8	90.3	92.7
3	11.3	15.1	49.4	50.8	43.2	42.2	47.1	43.7	9.4	7.0
4	2.9	3.7	22.9	21.9	42.5	42.3	41.5	42.8	0.3	0.3
5	1.1	1.1	4.6	4.2	9.1	10.3	7.6	9.1	*	*
6	0.2	0.3	1.2	0.8	0.6	0.7	0.3	0.6	-	-
7	*	0.1	0.2	0.1	*	*	-	-	-	-
8	*	0.1	*	*	-	-	-	-	-	-
<b>Average</b>	<b>1.73</b>	<b>1.85</b>	<b>3.14</b>	<b>3.09</b>	<b>3.58</b>	<b>3.61</b>	<b>3.54</b>	<b>3.59</b>	<b>1.52</b>	<b>1.47</b>
HVI Trash 1/										
00	0.6	0.6	*	*	-	-	-	-	1.3	1.3
01	60.3	53.7	3.3	4.4	0.2	0.3	0.1	0.1	67.8	72.1
02	24.0	25.8	19.1	18.5	5.5	5.0	5.1	4.8	22.8	20.4
03	7.8	10.0	25.8	25.8	17.3	16.2	20.5	17.4	6.0	4.5
04	3.3	4.6	21.7	22.1	23.6	22.9	28.8	26.5	1.6	1.2
05	1.6	2.2	14.1	14.1	20.9	21.1	21.7	22.2	0.4	0.3
06	1.0	1.2	7.8	7.4	15.0	15.3	13.1	14.5	0.1	0.1
07	0.5	0.6	3.9	3.7	9.0	9.4	6.3	7.6	*	*
08	0.4	0.5	1.9	1.8	4.7	5.1	2.6	3.9	*	*
09	0.2	0.2	1.1	0.9	2.2	2.6	1.1	1.7	-	*
10	0.1	0.2	0.6	0.5	0.9	1.2	0.5	0.8	-	-
11	0.1	0.1	0.4	0.3	0.4	0.5	0.2	0.4	*	*
12	*	0.1	0.2	0.2	0.2	0.2	-	0.1	-	-
13	*	*	0.1	0.1	0.1	0.1	*	*	-	-
14	*	*	0.1	*	*	*	*	*	-	-
15	*	*	*	*	*	*	-	-	-	-
16	-	*	*	*	*	*	-	-	-	-
17	-	*	*	*	*	*	-	-	-	-
18 & Above	*	0.1	*	*	*	*	-	-	-	-
<b>Average</b>	<b>0.17</b>	<b>0.19</b>	<b>0.39</b>	<b>0.38</b>	<b>0.49</b>	<b>0.50</b>	<b>0.46</b>	<b>0.48</b>	<b>0.14</b>	<b>0.13</b>
UNIFORMITY 2/										
74 & Below	0.1	0.1	0.2	*	-	-	-	-	-	*
75	0.2	0.7	0.6	0.1	-	-	-	-	0.1	0.3
76	1.5	2.4	0.8	0.3	-	-	-	-	0.6	2.1
77	4.6	6.1	1.8	0.9	0.1	0.1	-	-	4.3	6.5
78	12.9	15.0	4.1	2.7	0.7	0.8	0.1	0.1	14.8	21.2
79	23.1	23.9	9.0	7.9	3.5	3.8	1.2	1.4	31.4	32.9
80	28.0	27.1	19.0	20.8	17.9	17.3	18.9	17.6	30.8	24.1
81	22.5	19.1	30.7	37.1	46.0	42.3	55.1	48.2	12.8	9.1
82	6.4	5.2	26.7	24.2	26.7	28.9	18.4	23.7	4.5	3.2
83	0.6	0.5	6.6	5.2	4.5	6.0	6.1	8.0	0.7	0.6
84	*	*	0.4	0.6	0.6	0.7	0.2	0.9	0.1	0.1
85 & Above	-	-	*	*	*	*	-	-	*	*
<b>Average</b>	<b>80.11</b>	<b>79.90</b>	<b>81.21</b>	<b>81.31</b>	<b>81.55</b>	<b>81.60</b>	<b>81.56</b>	<b>81.67</b>	<b>79.93</b>	<b>79.58</b>
Tenderable 3/	<b>84.4</b>	<b>80.3</b>	<b>79.0</b>	<b>86.2</b>	<b>90.6</b>	<b>91.0</b>	<b>92.3</b>	<b>93.4</b>	<b>93.1</b>	<b>93.1</b>
<b>SAMPLES CLASSIFIED</b>										
Week	26,921		133,050		102,387		2,594		21,195	
Season	35,646		1,235,980		246,584		4,989		39,769	

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. \* Less than 0.05 percent.



**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE**  
**For The Week Ending Oct 22, 2020**

Quality MIKE	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
2.4 & Below	-	*	-	-	-	-	-	-	-	-
2.5 - 2.6	0.1	0.2	-	-	-	-	-	-	-	-
2.7 - 2.9	1.4	1.3	*	*	-	-	-	-	-	-
3.0 - 3.2	3.2	2.8	*	*	*	*	*	*	-	-
3.3 - 3.4	3.5	2.9	*	*	0.1	0.1	1.1	0.5	-	0.1
3.5 - 3.6	5.4	4.8	0.1	0.1	1.1	0.9	1.6	1.2	0.4	0.5
3.7 - 4.2	38.1	36.3	14.6	14.2	23.5	21.7	12.3	14.8	15.3	12.0
4.3 - 4.9	46.5	49.4	79.3	79.5	68.9	69.3	79.1	77.6	79.1	80.3
5.0 - 5.2	1.6	2.1	5.6	5.8	6.2	7.5	5.8	5.9	4.8	6.8
5.3 & Above	0.1	0.2	0.3	0.4	0.3	0.5	*	*	0.5	0.2
<b>Average</b>	<b>4.16</b>	<b>4.20</b>	<b>4.53</b>	<b>4.53</b>	<b>4.46</b>	<b>4.49</b>	<b>4.51</b>	<b>4.52</b>	<b>4.53</b>	<b>4.56</b>
Leaf										
1 - 2	91.5	91.4	3.1	2.9	15.4	16.4	6.3	8.6	89.0	89.7
3	8.1	7.9	37.5	36.2	44.5	43.8	38.9	46.4	9.7	9.4
4	0.4	0.6	44.9	45.8	32.3	31.7	44.9	38.5	1.3	1.0
5	*	0.1	13.0	13.6	7.3	7.7	9.0	6.1	*	*
6	-	*	1.4	1.5	0.5	0.5	0.9	0.4	-	-
7	-	*	0.1	0.1	-	*	-	-	-	-
8	-	-	*	*	-	-	-	-	-	-
<b>Average</b>	<b>1.51</b>	<b>1.51</b>	<b>3.72</b>	<b>3.75</b>	<b>3.32</b>	<b>3.31</b>	<b>3.59</b>	<b>3.43</b>	<b>1.66</b>	<b>1.65</b>
HVI Trash 1/										
00	0.9	0.9	-	-	*	*	-	-	0.1	0.1
01	66.2	66.4	0.2	0.2	2.6	3.0	0.6	1.1	62.7	64.3
02	23.8	23.4	4.5	4.3	13.3	13.7	7.3	9.8	26.3	26.9
03	6.4	6.4	16.9	16.1	20.8	20.4	16.2	20.9	6.2	5.6
04	1.8	1.9	24.7	24.3	21.5	21.2	22.9	24.7	2.6	1.8
05	0.6	0.6	21.9	22.1	17.6	17.2	21.8	20.2	1.3	0.8
06	0.2	0.2	14.8	15.2	11.9	11.8	15.3	12.4	0.6	0.3
07	0.1	0.1	8.7	9.0	6.6	6.7	8.6	6.3	0.2	0.1
08	*	*	4.5	4.7	3.2	3.3	4.0	2.7	*	*
09	*	*	2.1	2.2	1.4	1.5	1.8	1.1	*	*
10	*	*	1.0	1.0	0.6	0.7	0.9	0.5	-	*
11	*	*	0.4	0.5	0.3	0.3	0.4	0.2	-	-
12	-	*	0.2	0.2	0.1	0.1	0.2	0.1	-	-
13	-	*	0.1	0.1	*	0.1	*	*	-	-
14	-	-	*	*	*	*	*	*	-	-
15	-	-	*	*	*	*	-	-	-	-
16	-	-	*	*	-	-	-	-	-	-
17	-	-	*	*	-	-	-	-	-	-
18 & Above	-	-	*	*	-	-	-	-	-	-
<b>Average</b>	<b>0.14</b>	<b>0.15</b>	<b>0.49</b>	<b>0.50</b>	<b>0.43</b>	<b>0.43</b>	<b>0.48</b>	<b>0.44</b>	<b>0.16</b>	<b>0.15</b>
UNIFORMITY 2/										
74 & Below	*	*	-	-	-	-	-	-	-	-
75	0.2	0.3	*	*	-	-	-	-	-	-
76	1.0	1.3	*	*	*	*	-	-	-	-
77	3.3	4.6	0.4	0.4	*	*	-	*	*	*
78	9.9	12.6	2.6	2.7	0.1	0.1	0.4	0.3	0.5	0.3
79	22.4	24.3	11.3	11.6	1.2	1.1	4.1	3.0	6.7	5.3
80	30.1	28.6	32.5	33.2	11.6	11.0	12.9	12.8	29.4	30.4
81	23.3	20.3	34.8	34.1	38.0	37.0	32.4	31.7	41.6	44.2
82	8.3	6.9	14.8	14.3	36.7	37.2	38.3	39.5	6.0	12.1
83	1.3	1.1	3.2	3.2	10.8	11.9	10.9	11.5	10.0	4.6
84	0.1	0.1	0.4	0.4	1.4	1.5	1.0	1.2	5.6	2.9
85 & Above	*	*	*	*	0.1	0.1	0.1	0.1	0.2	0.1
<b>Average</b>	<b>80.32</b>	<b>80.12</b>	<b>81.03</b>	<b>81.01</b>	<b>81.94</b>	<b>81.97</b>	<b>81.86</b>	<b>81.92</b>	<b>81.45</b>	<b>81.34</b>
Tenderable 3/	<b>83.8</b>	<b>83.2</b>	<b>67.6</b>	<b>66.1</b>	<b>91.7</b>	<b>90.1</b>	<b>83.3</b>	<b>87.2</b>	<b>94.6</b>	<b>92.3</b>
<b>SAMPLES CLASSIFIED</b>										
Week	111,441		83,064		201,166		55,684		14,457	
Season	166,414		116,758		332,968		147,230		34,460	

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. \* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE**  
**For The Week Ending Oct 22, 2020**

Color Grade	Leaf	VISALIA			Quality Designation	VISALIA	
		Week	Season			Week	Season
01	1	8.7	22.3		MIKE		
	2	7.7	10.3		2.4 & Below	-	-
	3	0.1	*		2.5 - 2.6	-	-
	4	-	-		2.7 - 2.9	-	-
	5	-	-		3.0 - 3.2	-	-
	6	-	-		3.3 - 3.4	-	4.6
	7	-	-		3.5 - 3.6	3.5	28.7
<b>Total -----</b>		<b>16.5</b>	<b>32.7</b>		3.7 - 4.2	38.8	40.4
02	1	52.3	41.1		4.3 - 4.9	57.7	26.3
	2	26.5	23.5		5.0 - 5.2	-	-
	3	2.6	1.5		5.3 & Above	-	-
	4	-	-		<b>Average</b>	<b>4.15</b>	<b>3.86</b>
	5	-	-		ALL RANGE MIKE		
	6	-	-		2.4 & Below	-	-
	7	-	-		2.5	-	-
<b>Total -----</b>		<b>81.5</b>	<b>66.2</b>		2.6	-	-
03	1	1.2	0.5		2.7	-	-
	2	0.3	0.4		2.8	-	-
	3	0.4	0.2		2.9	-	-
	4	0.2	0.1		3.0	-	-
	5	-	-		3.1	-	-
	6	-	-		3.2	-	-
	7	-	-		3.3	-	1.1
<b>Total -----</b>		<b>2.0</b>	<b>1.2</b>		3.4	-	3.5
04	1	-	-		3.5	-	14.8
	2	-	-		3.6	3.5	13.9
	3	-	-		3.7	5.6	16.3
	4	-	-		3.8	7.0	10.2
	5	-	-		3.9	17.4	9.9
	6	-	-		4.0	6.2	2.8
	7	-	-		4.1	*	*
<b>Total -----</b>		<b>-</b>	<b>-</b>		4.2	2.5	1.2
05	1	-	-		4.3	30.0	13.7
	2	-	-		4.4	26.3	12.0
	3	-	-		4.5	0.8	0.3
	4	-	-		4.6	0.7	0.3
	5	-	-		4.7	-	-
	6	-	-		4.8	-	-
	7	-	-		4.9	-	-
<b>Total -----</b>		<b>-</b>	<b>-</b>		5.0	-	-
06	1	-	-		5.1	-	-
	2	-	-		5.2	-	-
	3	-	-		5.3 & Above	-	-
	4	-	-		<b>Average</b>	<b>4.15</b>	<b>3.86</b>
	5	-	-		STRENGTH 1/		
	6	-	-		36 & Below	0.1	1.0
	7	-	-		37	6.2	22.3
<b>Total -----</b>		<b>-</b>	<b>-</b>		38	19.2	39.9
07	1	-	-		39	12.5	8.4
	2	-	-		40	1.2	0.6
	3	-	-		41	0.1	0.1
	4	-	-		42	0.7	0.3
	5	-	-		43	12.8	5.8
	6	-	-		44	35.7	16.3
	7	-	-		45	9.2	4.2
<b>Total -----</b>		<b>-</b>	<b>-</b>		46	2.1	1.0
STAPLE	44 & Shorter	0.1	1.8		47	*	*
	46	34.6	66.6		48 & Above	0.1	*
	48	25.6	13.5		<b>Average</b>	<b>42.17</b>	<b>39.98</b>
	50	39.6	18.1		UNIFORMITY		
	52 & Longer	0.1	*		83 & Below	-	0.4
	<b>Average Staple</b>	<b>48.10</b>	<b>46.96</b>		84	11.1	42.5
Average Length		1.40	1.37		85	32.6	31.3
EXTRANEEOUS MATTER	Bark	*	*		86	45.1	20.6
	Grass	-	-		87	11.1	5.1
	Spindle Twist	0.2	0.1		88 & Above	0.1	*
	Preparation	*	*		<b>Average</b>	<b>85.99</b>	<b>85.34</b>
	All Other	*	*		Samples Classed		
					Week	2,256	
				Season		4,943	

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

\* Less than 0.05 percent.